

Content

Carbon, Low Alloy Steel Stahl, unlegiert / niedrig legiert	2.1.1 - 2.1.22 2.1.1 - 2.1.22
Stainless Steel, low Ni Edelstahl, niedrig legiert	2.2.1 - 2.2.5 2.2.1 - 2.2.5
Stainless Steel, aust. / Edelstahl, aust. Stainless Steel, high alloy / Edelstahl, hoch legiert	2.3.1 - 2.3.12 2.3.1 - 2.3.12
High Speed Steel / Schnellarbeitsstahl Toolsteel / Werkzeugstahl	2.4.1 - 2.4.5 2.4.1 - 2.4.5
Special Steel / Spezialstahl	2.5.1 - 2.5.6
Fe - Binary Standards / Fe - Binärstandards	2.6.1
Pure Iron / Reineisen	2.7.1 - 2.7.2
Steel, Control Chart Samples Stahl, Kontrolproben	2.8.1 - 2.8.2 2.8.1 - 2.8.2
Steel, SUS / Stahl, SUS	2.9.1 - 2.9.4



CRM	C	Mn	Si	P	S	Cr	Ni	Mo	V	W	Cu	Al	Al(sol)	Ti	Zr	Co	B	Nb
1 180B	(0.003)	0.047	0.001	0.004	0.0038	0.013	0.018	0.001	0.000	(0.0001)	0.006	(0.001)	-	0.000	0.000	0.003	0.0000	(0.0001)
1 181A	0.225	0.971	0.435	0.039	0.007	0.660	0.725	0.385	0.302	0.188	0.093	0.016	0.014	0.149	0.001	0.050	0.0069	0.058
1 182A	1.38	0.370	0.123	0.008	0.006	0.122	2.82	0.011	0.027	0.016	0.293	0.023	0.017	0.004	0.001	0.171	0.0003	0.001
1 183A	0.047	1.74	1.02	0.009	0.012	0.204	1.09	0.036	0.004	0.354	0.568	0.15	0.14	0.003	0.078	0.119	0.0005	0.006
1 184A	1.013	2.23	0.348	0.028	(0.01)	2.33	0.250	0.016	0.017	(0.001)	0.089	0.022	0.016	0.010	(0.002)	0.007	0.0005	0.013
1 185A	0.566	0.715	0.230	0.024	(0.02)	0.032	3.84	0.123	0.178	(0.001)	0.179	0.060	0.054	0.022	0.002	0.032	0.0116	0.20
1 186B	0.382	1.299	1.41	0.012	0.007	1.50	1.57	0.251	0.020	0.054	0.227	0.042	0.038	0.044	(0.002)	0.006	0.0009	0.004
1 187B	0.119	0.529	0.577	0.035	0.014	3.51	0.085	0.565	0.558	0.67	0.036	0.027	0.025	0.099	0.013	0.071	0.0006	0.028
1 188A	0.332	0.169	0.775	0.006	0.033	5.11	0.445	1.28	0.802	0.091	0.057	0.093	0.083	0.034	0.052	0.006	0.0047	0.122
1 189A	0.175	0.262	0.286	0.032	0.051	1.065	5.34	0.837	0.054	1.30	0.060	0.041	0.039	0.326	0.005	0.007	0.0030	0.017

Ta	Sn	As	Sb	Pb	Bi	N	Fe	Ø 44x25 mm + 44x13 mm, wrought
(0.0000)	0.0011	0.0010	0.0004	(0.0002)	(0.0000)	(0.0028)	(99.9)	Stahl, unleg/niedr. leg.
0.039	0.113	0.027	0.016	0.0005	-	(0.005)	(95.48)	Carbon/Low Alloy Steel
0.000	0.004	0.005	0.001	(0.000)	-	0.0049	(94.60)	
(0.000)	0.051	0.005	0.001	(0.000)	0.0000	0.0036	(94.49)	
0.000	0.008	0.006	0.002	(0.000)	-	0.0104	(93.58)	
0.085	0.003	0.022	0.011	0.002	-	0.0051	(93.63)	
0.009	0.018	0.007	0.002	(0.000)	-	(0.005)	(93.12)	
0.017	0.013	(0.007)	0.022	0.003	0.003	0.0122	(92.98)	
0.022	0.005	(0.005)	0.006	0.001	-	0.0076	(90.53)	
(0.005)	0.029	0.080	(0.003)	0.002	-	(0.004)	(90.01)	

CRM	C	Mn	Si	P	S	Cr	Ni	Mo	V	W	Cu	Al	Al(sol)	Ti	Zr	Co	B	Nb
1 181B	0.240	0.988	0.445	0.042	0.008	0.669	0.737	0.395	0.307	0.188	0.095	0.016	0.014	0.155	0.001	0.050	0.0076	0.062
1 182B	1.39	0.370	0.126	0.008	0.006	0.122	2.82	0.011	0.027	0.016	0.293	0.023	0.017	0.004	0.001	0.171	0.0003	0.001
1 183B	0.050	1.76	1.03	0.010	0.012	0.204	1.10	0.036	0.004	0.347	0.575	0.150	0.141	0.003	0.082	0.119	0.0005	0.006
Ta	Sn	As	Sb	Pb	Bi	N	Fe	Ø 44x25 mm + 44x13 mm, wrought										
0.042	0.122	0.029	0.017	0.0005	-	(0.005)	(95.37)	Stahl, unleg./niedr. leg.										
0.000	0.004	0.005	0.001	(0.000)	-	0.0049	(94.59)	Carbon/Low Alloy Steel										
(0.000)	0.054	0.004	0.001	(0.000)	0.0000	0.0036	(94.44)											

CRM	C	Mn	Si	P	S	Ni	Cr	Cu	Mo	V	Ti	Co	W	Al	As	Sn	Ø 45x30, wrought Nb Fe
1 163E	1.32	0.22	0.89	0.027	0.024	0.07	0.07	0.17	0.02	0.00	0.09	0.01	0.000	0.01	0.036	0.013	(0.00) (96.9)

CRM	C	S	P	Si	Mn	Cr	Ni	Cu	Mo	Ti	V	Al	As	B	Nb	Co		
2 A11/1	0.043	0.0137	0.011	1.46	0.21	0.02	0.04	0.047	1.08	0.17	0.46	0.02	-	-	0.16	-		
2 A12	0.031	0.082	0.014	1.19	0.31	1.25	2.43	0.18	0.47	0.05	0.042	0.18	0.007	-	(0.03)	0.012		
2 A13	0.104	0.073	0.053	0.81	0.49	0.14	1.93	0.166	0.91	0.11	0.23	0.042	0.070	(0.002)	-	0.011		
2 A14	0.12	0.052	0.041	0.73	0.75	0.59	1.32	0.20	0.25	0.12	0.67	(0.01)	0.13	0.004	0.044	0.070		
	Sn	Sb	Ø 35x19 mm, cast															
	0.002	(<0.001)	Stahl, niedr. leg.															
	-	0.013	Low Alloy Steel															
	0.060	0.024																
	0.10	0.047																
CRM	C	S	P	Si	Mn	Cr	Ni	Cu	Mo	Ti	V	Al	As	B	Nb	Sn	Pb	
2 A15	0.34	0.042	0.071	0.70	0.99	0.79	0.32	0.29	0.55	0.09	0.80	0.03	0.06	0.008	0.16	0.13	(0.004)	
2 A17	0.78	0.024	0.039	0.37	1.79	0.24	0.59	0.53	0.074	0.022	0.15	0.016	0.032	(0.012)	0.043	0.05	-	
2 A18	1.16	0.007	0.014	0.15	1.99	0.90	0.125	0.066	-	0.011	0.10	(0.02)	0.003	(0.011)	0.035	0.016	-	
2 A19/1	0.22	0.016	0.019	0.33	0.84	1.04	0.11	0.11	0.012	0.23	0.34	0.10	-	0.006	0.12	0.004	-	
	Sb	Co	Ø 35x19 mm, cast															
	-	-	Stahl, niedr. leg.															
	(0.10)	0.039	Low Alloy Steel															
	0.005	-																
	(<0.001)	-																
CRM	C	Si	Mn	S	P	Cu	Ni	Cr	V	Ti	Mo	W	Zr	Al	Ø 35x19 mm, cast			
2 B2/1	0.067	0.34	1.34	0.046	0.047	0.24	1.49	-	0.91	0.22	1.09	-	-	0.82	Stahl. niedr. leg.			
2 B3	0.20	0.53	0.14	0.025	(0.012)	0.25	-	5.94	1.16	-	-	1.19	-	-	Low Alloy Steel			
2 B4	0.55	1.72	1.07	0.043	0.047	0.49	-	-	-	-	-	-	0.09	-				
CRM	C	S	P	Si	Mn	Cr	Ni	Cu	Mo	Ti	V	Co	Al	As	B	Nb	Sn	Ø 35x19mm
2 B12	0.43	0.048	0.028	0.34	0.76	1.32	1.62	0.41	0.21	0.011	0.026	0.011	0.007	0.011	0.0035	0.022	0.032	Stahl, niedr.leg LA-Steel
2 B14	1.16	0.005	0.028	1.21	0.65	3.17	0.16	0.107	1.25	0.26	0.14	0.30	-	-	0.0006	0.41	-	
2 B15	0.89	0.031	0.030	0.80	0.69	3.70	0.15	0.14	1.20	0.32	0.33	0.21	0.13	-	-	-		
2 B16	0.16	0.051	0.068	1.95	2.05	0.26	3.74	0.09	0.11	0.075	0.53	-	0.037	-	-	0.11	-	
2 B20	0.008	0.013	0.012	0.005	0.09	0.03	0.038	0.034	(<0.01)	(<0.002)	(<0.005)	(<0.01)	(0.01)	(0.003)	-	-	-	
CRM	C	S	P	Si	Mn	Cr	Ni	Cu	Mo	Ti	V	W	Co	Al	B	Ø 35x19 mm, cast		
2 E20	0.19	0.003	0.017	0.71	(1.1)	(1.6)	0.68	0.25	0.22	0.27	(0.7)	0.18	(0.02)	0.04	(0.007)	Stahl, niedr. leg.		
2 E23	(1.3)	0.002	0.014	0.86	0.33	0.34	0.08	0.18	0.02	0.02	(0.04)	(0.01)	0.03	0.01	(0.006)	Low Alloy Steel		

CRM	C	S	P	Si	Mn	Cr	Ni	Cu	Mo	Ti	V	Al	Nb	Ø 35x19 mm, cast				
2 K3	1.03	0.010	(0.02)	0.32	0.46	1.63	0.18	0.09	-	-	-	-	-	Kugellagerstahl; Ball Bearing Steel				
2 K4	0.52	0.025	(0.02)	0.46	0.84	1.24	(0.1)	0.28	-	-	0.20	-	-	Federstahl; Spring Steel				
2 K9	0.096	0.018	(0.01)	0.59	1.53	0.64	0.97	0.73	0.56	0.11	0.27	(0.01)	(0.04)	Baustahl; Construction Steel				
CRM	C	Mn	P	S	Si	Cu	Ni	Cr	B	Pb	Ag	Ti	O	N	H	V	Mo	
3 1262B	0.160	1.05	0.044	0.037	0.40	0.51	0.59	0.30	0.0025	0.0004	0.0011	0.100	(0.0011)	(0.0040)	(<0.0005)	0.041	0.070	
3 1264A	0.87	0.258	0.010	0.025	0.067	0.250	0.142	0.066	(0.011)	0.024	(0.00002)	0.24	(0.0010)	(0.0032)	(<0.0005)	0.106	0.49	
3 1265A	0.0067	0.0057	0.0011	0.0055	0.0080	0.0058	0.041	0.0072	0.00013	0.15ppm	<0.2ppm	(0.0001)	<70ppm	<20ppm	<5ppm	0.0006	0.0050	
	W	Co	As	Sn	Al	Nb	Ta	Zr	Sb	Bi	Ca	Mg	Se	Te	Zn	Au	Ce	
0.20	0.30	0.096	0.016	0.081	0.30	0.20	0.22	0.012	(0.002)	(0.0001)	0.0006	(0.0012)	(0.001)	(0.0005)	(0.00005)	0.0019		
0.102	0.15	0.052	(0.008)	(0.0080)	0.157	0.11	0.069	0.034	(0.0009)	0.00004	0.00015	(0.00021)	0.00018	(0.001)	0.0001	0.00022		
<1ppm	0.0070	(0.0002)	<3ppm	(0.0007)	-	(<0.5ppm)	(<0.1ppm)	(<0.5ppm)	(<0.1ppm)	(<0.1ppm)	(<0.2ppm)	(<0.1ppm)	(<0.1ppm)	<2ppm	(<0.02ppm)	(<0.05ppm)		
	La	Nd	Ø 31x19 mm															
(0.0004)	0.0006	AISI 94B17																
0.00007	0.00007	High C																
(<0.05ppm)	(<0.05ppm)	Electrolyt. Iron																
CRM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Co	Sn	Al	V	Ti	Nb	Zr	As	N
3 1762	0.337	0.35	0.030	0.033	2.00	1.15	0.92	0.35	0.120	0.062	0.046	0.069	0.200	0.095	0.070	0.029	0.018	0.0022
3 1763A	0.202	0.633	0.022	0.0123	1.584	0.513	0.498	0.490	0.042	0.093	(0.011)	0.0435	0.307	0.308	0.100	0.044	0.055	0.0045
3 1765	0.006	(0.004)	0.0038	0.0052	0.144	0.154	0.051	0.0055	0.0013	0.0012	0.002	(0.006)	0.0040	0.0055	0.0004	(0.0002)	0.0010	0.0010
3 1766	0.015	0.010	0.0024	0.002	0.067	0.021	0.024	0.0035	0.015	0.0020	0.0010	0.012	0.009	0.0005	0.005	(0.0004)	0.0035	0.0033
3 1767	0.052	0.026	0.0090	0.0031	0.022	0.002	0.0015	0.020	0.0014	0.0050	0.006	0.004	0.033	0.011	0.010	(0.004)	0.0005	0.0008
	Ta	ppm Pb	ppm Ag	ppm Bi	ppm Ca	ppm B	ppm Sb	ppm Mg	ppm Te	ppm Se	ppm Ce	ppm W	Ø 34x19, wrought					
0.021	-	-	-	-	49	-	-	-	-	-	-	-						
(0.012)	-	-	-	-	54	110	-	-	-	-	-	(20)						
(0.004)	3	2	(<1)	-	9	10	(<1)	(30)	(35)	-	-	-						
(0.006)	30	5	(<1)	-	1.2	5	(<5)	(30)	(35)	(20)	(10)							
(0.002)	(<1)	8	(<1)	(3)	10	20	(<1)	(30)	-	-	-							
3 1765, 1766 + 1767	Späne lieferbar;	Chips available																
CRM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Ca	Ø 31x19 mm, wrought							
3 1254	(0.03)	(0.28)	(0.03)	(0.008)	(2.9)	(0.07)	(0.04)	(0.02)	(0.008)	0.0053	Stahl, kalziumbeh.; Steel, Calcium treated							
CRM	C	Mn	P	S	Si	Cu	Ni	Cr	V	Mo	Al	Ø 31x19 mm, wrought						
3 1224	0.75	0.41	0.009	0.039	0.173	0.072	0.054	0.071	0.002	0.013	0.060	AISI 1078						
3 1225	0.274	0.48	0.007	0.014	0.221	-	0.018	0.91	0.004	0.166	-	AISI 4130						

CRM	C	Mn	P	S	Si	Cu	Ni	Cr	V	Mo	Co	Ti	Sn	Al	As	Nb	Ø 31x19 mm, wrought
3 1226	0.085	0.274	0.0022	0.0044	0.231	0.125	5.42	0.467	0.0018	0.446	0.029	0.0021	(0.003)	0.054	-	-	Low Alloy
3 1227	0.97	0.402	0.014	0.026	0.215	0.006	0.007	0.019	0.002	0.003	0.003	(0.0008)	-	(0.028)	-	-	1% C
3 1228	0.072	0.365	0.004	0.018	0.007	0.012	0.018	0.016	<0.001	0.009	-	-	-	0.061	-	-	0.1% C
3 1269	0.298	1.35	0.012	0.0061	0.189	0.095	0.108	0.201	0.004	0.036	-	-	0.005	0.016	-	-	AISI 1526
3 1270	0.077	0.626	0.0065	0.0065	0.247	0.114	0.174	2.34	0.013	0.956	0.038	-	-	-	-	-	Low Alloy
3 1271	0.064	0.73	0.005	0.0013	0.334	1.48	3.34	0.552	0.003	0.543	-	-	-	0.020	-	0.025	HSLA 100
3 1286	0.196	0.152	0.008	0.017	0.130	0.043	2.81	1.53	0.0057	0.344	0.116	0.040	0.012	0.109	0.019	-	Hy 80

3 1218 + 1222 Späne lieferbar; Chips available

CRM	C	Mn	P	S	Si	Cu	Ni	Cr	V	Mo	Co	Ce	Sn	Ø 31x19 mm, chill cast				
3 C1285	0.058	0.332	0.072	0.020	0.36	0.37	1.17	0.80	0.150	0.164	0.036	(0.0213)	0.035	A 242 Mode Stahl, niedr. leg.; Low Alloy Steel				
CRM	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Sn	Ti	V
5 111	0.028	0.0253	0.155	0.0033	0.0054	0.0197	0.0008	0.0387	0.0348	0.0021	<0.001	0.0144	0.0171	0.0034	(0.0005)	0.0015	0.0004	0.0009
5 112	0.394	0.289	0.436	0.0043	0.0026	1.236	0.190	1.461	0.0148	0.0021	0.0007	0.0175	0.149	0.0024	0.0065	0.0086	0.0100	0.0088
5 113	0.837	0.931	1.207	0.0595	0.0294	1.248	0.056	0.0784	0.0151	0.0020	0.0066	0.0415	0.179	0.0109	0.0487	0.0067	0.0390	0.201
5 114	0.403	0.295	0.416	0.0044	0.0046	0.187	0.184	1.502	0.078	0.0025	0.0008	0.0171	0.358	0.0043	0.0042	0.041	0.0096	0.0086

W Zr 44x19 mm, wrought

- (<0.001) Stahl, niedr. leg.
 - (<0.001) Low Alloy Steel
 0.012 0.0029
 (<0.001) 0.0051

5 111, 112, 113 + 114 Späne lieferbar; Chips available

CRM	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Cu	Nb	Ø 38x19 mm, wrought
5 432/1	0.102	0.043	1.34	0.024	0.039	0.31	(0.02)	0.14	(0.01)	(0.04)	<0.002	Kohlenstoffstahl
5 433/1	0.195	0.18	0.60	0.074	0.069	0.26	(0.01)	0.064	(<0.01)	(0.06)	0.020	Carbon Steel
5 434/1	0.41	0.31	1.49	0.050	0.027	0.055	(0.01)	0.044	(<0.01)	(0.05)	0.078	
5 435/1	0.52	0.54	0.41	0.033	0.031	0.14	(<0.01)	0.060	(<0.01)	(0.05)	0.039	

CRM C Si Mn P S Cr Ni Co N Nb Ø 38x19 mm, wrought

5 431/2	0.026	0.015	0.90	0.12	0.006	0.050	0.040	-	0.005	0.004	Kohlenstoffstahl
5 432/2	0.008	0.08	0.70	0.017	0.036	0.016	0.019	-	0.007	0.018	Carbon Steel
5 433/2	0.095	0.005	1.19	0.012	0.008	0.026	0.38	-	-	0.06	
5 434/2	0.27	0.51	1.54	0.06	0.014	0.24	0.38	-	0.010	0.038	
5 435/2	0.49	0.32	0.39	0.04	0.042	0.18	0.13	0.011	-	0.13	

CRM C Si Mn P S Al Al(sol) B Co Nb Pb V Zr Sb Ø 38x19 mm, wrought

5 456/2	0.112	0.297	0.220	0.0212	0.0221	0.0017	(0.0013)	0.0015	0.0504	0.0057	0.0189	0.0221	(0.014)	0.0172	Kohlenstoffstahl
5 457/2	0.307	0.105	0.327	0.0098	0.0448	0.088	0.084	0.0046	0.0217	0.0174	0.0098	0.153	0.025	0.050	Carbon Steel
5 458/2	0.198	0.504	0.479	0.0281	0.0314	0.055	0.053	0.0069	0.198	0.0510	0.0140	0.105	(0.064)	0.089	
5 459/2	0.467	0.640	0.909	0.0482	0.0481	0.015	(0.013)	0.0110	0.0890	0.0102	0.0044	0.0585	(0.074)	0.0121	
5 460/2	0.383	0.126	0.616	0.0374	0.0099	0.024	(0.019)	0.0027	0.0106	0.068	0.0005	0.0322	(<0.0005)	(0.0006)	

CRM	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Cu	V	Co	N	Ø 38x19 mm, wrought		
5 401/2	0.935	0.602	1.197	0.0265	0.0078	0.138	0.499	0.019	0.074	0.101	0.496	0.0041	(0.015)	Stahl, niedr. leg. Späne lieferbar		
5 402/2	1.311	0.111	0.228	0.0157	0.0138	0.652	0.140	0.809	0.161	0.302	0.194	-	0.0069	Low Alloy Steel Chips available		
5 403/2	0.750	0.209	1.68	0.055	0.038	0.463	0.088	0.223	0.049	0.221	0.341	-	(0.010)			
5 404/2	0.696	1.121	0.532	0.0479	0.0228	0.774	0.307	0.393	0.018	0.428	0.107	-	0.0089			
5 405/2	0.044	0.947	0.903	0.0095	0.0585	0.206	0.025	0.102	0.304	0.022	0.411	(0.009)	(0.011)			
CRM	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Co	Cu	N	Pb	V	Ø 38x19 mm, wrought
5 406/2	0.173	0.342	0.447	0.0102	0.043	2.001	0.98	1.62	0.013	0.012	-	0.289	-	0.0002	0.010	Stahl, niedr. leg.
5 407/2	0.490	0.66	0.195	0.038	0.0105	3.03	0.83	0.527	0.040	-	0.0068	0.397	-	-	0.19	Low Alloy Steel
5 408/2	0.289	0.237	0.557	0.056	0.030	0.111	0.098	4.13	0.154	0.0046	-	0.694	0.0075	0.0006	0.067	
5 409/2	0.086	1.18	0.559	0.0141	0.0179	1.318	0.599	3.02	0.094	-	-	0.205	0.0108	-	0.008	
5 410/2	0.428	1.10	0.419	0.074	0.041	1.684	0.432	2.07	0.046	0.0053	0.0248	0.436	0.0155	-	0.44	
5 406 - 410 Späne lieferbar; Chips available																
CRM	C	Si	Mn	P	S	Al	Cr	Mo	Ni	Co	Cu	V	Zr	Ø 44x19 mm, cast		
5 601/2	0.102	0.263	1.30	0.034	0.024	0.033	(0.14)	(0.006)	(0.03)	(0.09)	(0.04)	(0.002)	(<0.005)	Kohlenstoffstahl		
5 602/2	0.94	0.057	0.66	0.023	0.031	0.096	(0.03)	(0.004)	(0.02)	(0.007)	(0.06)	(0.001)	(<0.005)	Carbon Steel		
5 603/2	0.78	0.97	0.236	0.020	0.056	0.076	(0.04)	(0.004)	(0.03)	(0.01)	(0.05)	(0.001)	(<0.005)			
5 604/2	0.199	0.75	1.91	0.016	0.072	0.008	(0.06)	(0.02)	(0.09)	(0.01)	(0.07)	(0.001)	(<0.005)			
5 605/2	0.400	0.54	0.345	0.054	0.015	0.027	(0.06)	(0.01)	(0.05)	(0.008)	(0.06)	(0.001)	(0.12)			
CRM	C	Si	Mn	Ni	Cr	Mo	V	S	Cu	Ø 44x19 mm, cast						
5 612/1	0.12	0.28	0.60	0.97	4.14	0.80	0.21	(0.02)	(0.06)	Stahl, niedr. leg.						
5 614/1	0.41	0.39	1.30	3.05	1.18	0.60	0.27	(0.02)	(0.06)	Low Alloy Steel						
5 615/1	0.30	0.17	1.68	4.01	0.49	0.21	0.10	(0.02)	(0.05)							
CRM	C	Si	Mn	P	S	Ni	Cr	Cu	Ø 35x30 mm, wrought							
9 410	0.099	0.116	0.43	0.029	0.030	0.011	0.011	0.102	Kohlenstoffstahl							
9 411	0.138	0.117	0.43	0.029	0.030	0.011	0.010	0.101	Carbon Steel							
9 412	0.196	0.117	0.43	0.029	0.030	0.011	0.011	0.101								
9 413	0.39	0.25	0.56	0.019	0.019	0.011	0.011	0.102	nur Satz/set only							
9 414	0.61	0.25	0.55	0.019	0.019	0.011	0.013	0.102								
9 415	0.75	0.25	0.55	0.019	0.019	0.011	0.013	0.101								

CRM	C	Si	Mn	P	S	Cr	Ni	Cu	Co	As	Ø 38x45 mm, wrought			
CI 11751	0.661	1.82	0.805	0.027	0.017	0.021	0.020	0.136	0.011	0.016	Stahl, niedr. leg.; Low Alloy Steel			
CRM	C	Si	Mn	P	S	Cr	Ni	Cu	Al	Ø 34x34 mm, wrought				
CM 5050	0.108	0.029	1.15	0.0038	0.070	0.379	0.252	0.276	0.073	Kohlenstoffstahl				
CM 5051	0.172	0.103	1.07	0.014	0.012	0.241	0.210	0.14	-	Carbon Steel				
CM 5052	0.29	0.156	0.62	0.032	0.026	0.153	0.181	0.193	-					
CM 5053	0.30	0.247	0.86	0.023	0.040	0.092	0.065	0.097	-	nur Satz/set only				
CM 5054	0.44	0.46	0.41	0.039	0.040	0.275	0.062	0.325	0.40					
CM 5055	0.58	0.374	0.163	0.054	0.0033	0.34	0.343	0.38	0.463					
CRM	C	Si	Mn	P	S	Cr	Ni	Cu	Al	Mo	Ti	Ø 38x48 mm, wrought		
CM 5057	0.181	0.235	0.617	0.0265	0.009	0.062	0.426	0.256	0.11	0.004	-	Kohlenstoffstahl		
CM 5058	0.465	0.338	0.206	0.046	0.037	0.087	0.174	0.086	0.26	0.007	0.003	Carbon Steel		
CM 5059	0.276	0.137	0.412	0.0133	0.012	0.090	0.245	0.034	0.20	0.004	-			
CM 5060	0.583	0.387	0.110	0.037	0.046	0.188	0.079	0.077	0.18	0.007	0.0034	nur Satz/set only		
CM 5061	0.371	0.467	0.394	0.031	0.031	0.290	0.109	0.137	0.24	0.007	0.0035			
CM 5062	0.087	0.692	0.209	0.0051	0.010	0.491	0.041	0.392	0.075	0.004	0.0064			
CRM	C	Si	Mn	P	S	Ni	Cr	W	V	Mo	Al	Ti	Cu	Ø 35x35 mm, wrought
CM 5063	0.692	0.282	0.712	0.028	0.0126	0.507	0.280	0.155	0.108	0.160	0.019	0.132	0.161	Kohlenstoffstahl
CM 5064	0.982	0.368	0.342	0.0132	0.0308	0.394	0.162	0.248	0.063	0.083	0.023	0.145	0.091	Carbon Steel
CM 5065	0.369	0.189	0.02	0.0172	0.0026	0.084	0.228	0.091	0.173	0.229	0.176	0.051	0.226	
CM 5066	0.056	0.031	0.058	0.0030	0.0257	0.025	0.493	0.382	0.242	0.303	0.072	0.012	0.283	nur Satz/set only
CM 5067	1.27	0.517	1.27	0.0396	0.0252	0.215	0.094	0.033	0.049	0.014	0.130	0.168	0.063	
CM 5068	0.189	0.133	0.226	0.0449	0.0374	0.286	0.377	0.455	0.286	0.399	0.108	0.190	0.330	
CRM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	W	Ø 33x35 mm, wrought		
CM 5011	0.158	1.69	0.051	0.038	1.60	0.492	0.271	0.535	0.116	0.128	0.075	Stahl, niedr. leg., hoch SiMn		
CM 5012	0.471	0.855	0.026	0.051	0.98	0.301	0.386	0.042	0.223	0.209	0.155	Low Alloy Steel, high SiMn		
CM 5013	0.294	1.08	0.039	0.028	1.43	0.106	0.178	0.146	0.029	0.065	0.035			
CM 5014	0.221	1.37	0.014	0.006	1.18	0.102	0.104	0.310	0.034	0.016	0.015	nur Satz/set only		

CRM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Al(sol)	Ti	Ti(sol)	V	As	B	B(sol)
CI 11714-1	1.18	2.00	0.0053	0.031	0.421	0.033	0.161	4.47	0.027	0.159	0.154	0.460	0.456	0.016	0.021	0.021	0.010
CI 11714-2	0.076	0.095	0.027	0.010	0.966	0.216	0.988	1.89	1.09	0.858	0.850	0.259	0.256	0.241	0.0025	0.011	0.010
CI 11714-3	0.930	1.20	0.011	0.044	1.10	0.364	0.501	3.23	0.292	0.108	0.102	0.322	0.317	0.061	0.0070	0.015	0.013
CI 11714-4	0.499	0.798	0.029	0.021	2.14	0.303	1.97	0.974	0.030	0.027	0.025	0.082	0.079	0.469	0.0072	0.0047	0.0043
CI 11714-5	0.717	1.61	0.040	0.0020	0.089	0.076	4.27	0.168	0.570	1.11	1.09	0.142	0.137	0.125	0.0048	(0.0006)	(0.005)
CI 11714-6	0.257	0.428	0.030	0.010	0.729	0.145	2.84	0.578	0.171	0.704	0.697	0.225	0.221	0.339	0.011	0.0020	0.0018

Bi	Co	Pb	Sb	Sn	W	Nb	Zr	Ca	Ce	Ø 38x30 mm, wrought
0.086	0.032	(0.0003)	0.0007	0.0021	0.404	0.288	0.0044	0.0012	<0.0001	Stahl, niedrig leg.
0.0014	0.161	0.0021	0.0007	0.0016	2.07	0.206	0.045	0.0016	<0.0001	Low Alloy Steel
0.013	0.504	0.0023	0.0023	0.011	0.814	2.48	0.011	(0.0005)	<0.0001	
(0.0001)	0.238	0.017	0.0061	0.018	1.56	0.124	0.051	0.0012	<0.0001	nur Satz/set only
0.0032	0.075	0.020	0.018	0.0048	0.060	0.023	0.348	(0.0006)	<0.0001	
0.010	0.122	0.011	0.021	0.013	1.19	0.049	0.176	(0.0005)	<0.0001	

CRM	C	Si	Mn	P	S	Al	Al(sol)	B	B(sol)	Ø 35x32 mm, wrought
CI 15749	0.0045	1.57	0.247	0.010	0.0054	0.050	0.048	0.0026	0.0018	Stahl, niedr. leg., niedr. C-hoch Si Low Carbon Silicon Steel

CRM	C	Mn	P	S	Si	Cu	Ni	Cr	V	Ø 35x50 mm, wrought
CM 2031	0.21	0.23	0.012	0.004	0.13	0.32	3.50	0.025	0.37	Stahl, niedr. leg.
CM 2032	0.37	0.47	0.007	0.007	0.19	0.26	2.74	0.48	0.30	Low Alloy Steel
CM 2033	0.43	0.62	0.021	0.035	0.30	0.18	2.20	0.84	0.26	
CM 2034	0.52	0.82	0.015	0.028	0.24	0.13	1.72	1.23	0.19	nur Satz/set only
CM 2035	0.61	1.07	0.033	0.035	0.36	0.11	1.14	1.53	0.14	
CM 2036	0.70	1.30	0.032	0.022	0.45	0.07	0.52	1.86	0.07	

CRM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Ø 32x48 mm, wrought
CM 2061	0.196	0.543	0.0106	0.0101	0.447	0.082	0.460	2.22	0.476	0.383	Stahl, niedr. leg.
CM 2062	0.141	0.790	0.0102	0.0100	0.581	0.054	0.103	1.86	0.341	0.508	Low Alloy Steel
CM 2063	0.370	0.469	0.0166	0.0492	0.239	0.436	0.197	1.58	0.148	0.790	
CM 2064	0.706	0.196	0.0397	0.0375	0.224	0.070	0.479	1.97	0.391	0.247	nur Satz/set only
CM 2065	0.238	0.546	0.0268	0.0104	0.364	0.295	0.067	1.16	0.092	0.962	
CM 2066	0.532	0.421	0.0379	0.0093	0.310	0.120	0.045	0.99	0.044	1.38	

CRM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	Ti	W	Ca	Ø 30x50 mm, wrought
CM 2101	0.050	0.975	0.0036	0.0084	0.32	0.10	2.21	0.415	0.37	0.23	0.13	0.027	(0.005)	(0.0025)	Stahl, niedr. leg.
CM 2102	0.15	0.86	0.0057	0.022	0.145	0.14	3.04	0.76	0.21	0.14	0.036	0.060	(<0.001)	(0.0008)	Low Alloy Steel
CM 2103	0.31	0.71	0.026	0.0031	0.27	0.18	4.01	1.57	0.029	0.064	0.175	0.16	(0.007)	(0.0015)	
CM 2104	0.45	0.49	0.020	0.027	0.41	0.11	1.70	1.21	0.505	0.31	0.129	0.0099	(0.001)	(0.0027)	nur Satz/set only
CM 2105	0.63	0.31	0.039	0.047	0.125	0.30	1.04	1.94	0.083	0.39	0.258	0.195	(0.011)	(0.0004)	

CRM	C	Si	Mn	P	S	Cr	Mo	W	V	B	B(sol)	Ø 35x25 mm, wrought
CI 13704-1	0.068	0.510	1.096	0.012	0.047	0.281	1.46	0.298	0.394	0.0012	0.0010	Stahl, niedr. leg.
CI 13704-2	0.100	0.290	0.853	0.016	0.071	0.486	1.19	0.438	0.206	0.0021	0.0016	Low Alloy Steel
CI 13704-3	0.176	0.272	0.585	0.023	0.028	0.775	0.747	0.796	0.251	0.0038	0.0030	
CI 13704-4	0.193	0.173	0.396	0.039	0.027	1.19	0.472	1.44	0.061	0.0068	0.0058	nur Satz/set only
CI 13704-5	0.256	0.055	0.269	0.048	0.010	1.46	0.301	1.94	0.041	0.0090	0.0081	

CRM	C	Si	Mn	P	S	Cr	Ni	Cu	V	Ti	Mo	Al	Ø 30x47 mm, wrought
CI 16706-1	0.067	0.115	1.72	0.0095	0.0067	0.380	0.378	0.069	0.026	0.067	0.054	0.036	Stahl, niedr. leg.
CI 16706-2	0.032	0.061	1.48	0.013	0.0044	0.323	0.267	0.133	0.063	0.027	0.014	0.014	Low Alloy Steel
CI 16706-3	0.054	0.248	1.31	0.0046	-	0.252	0.070	0.273	0.155	0.167	0.121	0.026	
CI 16706-4	0.083	0.415	1.27	0.0049	-	0.117	0.058	0.333	0.210	0.117	0.207	0.111	nur Satz/set only
CI 16706-5	0.087	0.360	1.03	0.012	-	0.033	0.350	0.435	0.231	0.150	0.152	0.106	
CI 16706-6	0.112	0.244	1.40	0.019	0.0054	0.185	0.160	0.260	0.154	0.0068	0.078	0.092	

CRM	C	Si	Mn	P	S	Cr	Ni	W	Mo	Al	Ti	Cu	As	Sn	Pb	Sb	Ø 36x43 mm, wrought
CI 29710-1	0.780	0.692	0.313	0.016	0.0086	0.102	0.370	0.146	0.128	0.064	0.017	0.323	0.053	0.029	0.0018	0.013	Stahl, niedr. leg.
CI 29710-2	1.09	0.796	0.484	0.0055	0.0086	0.701	0.297	0.194	0.282	0.124	0.064	0.143	0.026	0.035	0.0035	0.0058	Low Alloy Steel
CI 29710-3	0.951	0.404	0.801	0.032	0.025	0.403	0.054	0.105	0.086	0.012	0.011	0.202	0.023	0.013	0.017	0.021	
CI 29710-4	0.690	0.619	0.118	0.011	0.041	1.37	0.152	0.317	0.185	0.053	0.026	0.237	0.022	0.019	0.0097	0.031	
CI 29710-5	1.02	0.273	0.954	0.018	0.033	0.957	0.093	0.023	0.024	0.024	0.0042	0.050	0.010	0.043	0.0067	0.016	
CI 29710-6	1.22	0.136	1.26	0.045	0.057	1.65	0.028	0.041	0.042	0.086	0.0064	0.099	0.0054	0.0017	(0.00023)	0.0010	

CRM	C	Si	Mn	P	S	Cr	Ni	Cu	V	Ti	Co	Al	B	W	Mo	Nb	Zr	Sb
CI 11756	0.208	0.360	0.394	0.051	0.041	0.185	0.208	0.201	-	-	-	0.501	0.0014	-	-	-	-	-
CI 11757	0.168	0.413	0.371	0.054	0.052	0.077	0.092	0.107	-	-	-	0.414	0.0044	-	-	-	-	-
CI 11758	0.166	0.254	0.393	0.026	0.025	0.092	0.101	0.124	-	-	-	0.183	0.0021	-	-	-	-	-
CI 11759a	0.127	0.219	0.481	0.017	0.024	0.0058	0.015	0.257	-	-	-	-	-	-	-	-	-	-
CI 11760a	0.169	0.47	1.29	0.025	0.014	0.045	0.052	0.311	-	-	0.015	0.071	-	-	0.022	-	-	0.006
CI 11761	0.397	0.401	0.555	0.024	0.022	0.238	0.188	0.133	-	-	-	0.466	0.0023	-	-	-	-	-
CI 11762	0.456	0.440	0.646	0.057	0.030	0.206	0.176	0.107	-	-	-	0.504	0.0022	-	-	-	-	-
CI 11763	0.543	0.361	0.663	0.024	0.024	0.169	0.164	0.118	-	-	-	0.089	0.0621	-	-	-	-	-
CI 11764	0.235	0.318	0.632	0.037	0.028	0.076	0.103	0.106	-	-	-	0.071	-	-	-	-	-	0.014
CI 11765	0.374	0.327	0.520	0.029	0.022	0.973	0.203	0.123	-	-	-	0.067	0.0022	-	0.238	-	-	-
CI 11766	0.225	0.386	1.04	0.012	0.016	1.06	0.122	0.174	-	0.073	-	0.096	0.0016	-	-	-	-	-
CI 11767	0.263	1.40	1.34	0.044	0.023	0.083	0.063	0.125	-	-	-	0.064	-	-	-	-	-	0.018
CI 11768	0.178	0.187	0.392	0.066	0.044	0.243	3.41	0.373	0.289	0.039	0.0066	0.151	0.0025	0.406	0.089	0.035	0.0082	0.0060
CI 11769	0.447	1.20	0.825	0.028	0.022	1.10	0.434	0.252	0.219	0.065	0.016	0.0070	0.015	0.015	0.036	0.096	0.0011	0.0018
CI 11770	0.803	0.882	0.294	0.020	0.031	2.76	0.140	0.055	0.144	0.132	0.228	0.194	0.0060	0.233	0.983	0.059	0.0010	0.020
CI 11771	0.238	0.290	0.712	0.014	0.015	1.05	1.42	0.154	0.013	0.0022	0.052	0.067	0.0015	0.057	0.164	0.0066	0.0011	-
CI 11772	0.542	0.647	1.69	0.030	0.025	0.756	1.08	0.162	0.214	0.044	0.063	0.132	0.0031	0.134	0.293	0.134	0.0012	0.0060

Sn As Pb Ø 37x45 mm, wrought

0.010 0.029 - **Stahl, niedr. leg.**
 0.0094 0.024 - **Low Alloy Steel**
 - - -
 - 0.012 0.0013
 0.0059 0.012 -
 0.0050 0.012 -
 0.0035 0.012 -
 0.0026 0.012 -
 0.024 0.015 0.0011
 0.0060 0.017 -
 0.0031 0.0055 -
 0.015 0.012 -
 0.023 0.0050 0.0004
 0.0063 0.023 0.0062
 0.0059 0.011 0.0062
 0.059 0.0079 0.0003
 0.030 0.017 0.020

B R E I T L Ä N D E R G M B H

2.1.10

Stahl, unleg. / niedr. leg. (Carbon / Low Alloy Steel)

CRM	C	Mn	Si	P	S	Cr	Ni	Cu	Mo	V	Ti	Nb	Al	Al(sol)	Sn	Sb	Pb
G 110	0.011	0.015	0.009	0.008	0.010	0.007	0.019	0.051	0.025	0.002	-	-	0.008	0.003	0.026	0.014	0.0010
G 111	0.106	0.31	0.55	0.010	0.039	0.072	0.23	0.036	0.084	0.022	-	-	0.017	0.007	-	-	-
G 112	0.195	0.43	0.27	0.022	0.016	0.034	0.046	0.055	0.043	0.045	0.010	0.013	0.034	0.024	0.15	-	-
G 113	0.24	0.50	0.10	0.022	0.025	1.25	0.13	0.11	0.050	0.039	-	-	0.007	0.004	-	-	-
G 114	0.35	1.16	0.33	0.024	0.021	0.42	0.10	0.51	0.11	0.096	(0.005)	-	(0.029)	0.018	0.008	(0.006)	0.033
G 115	0.36	0.65	0.043	0.045	0.024	0.27	0.35	0.25	0.070	(0.063)	-	0.009	(0.015)	(0.0058)	-	-	-
G 116	0.64	0.94	0.25	0.025	0.035	0.72	0.022	0.33	0.074	0.076	(0.0008)	-	0.025	0.012	-	-	-
G 117	0.49	0.77	0.34	0.038	0.015	0.94	0.29	0.41	0.024	0.087	(0.0014)	0.041	0.023	0.013	-	-	-
G 118	0.69	1.72	0.30	0.026	(0.049)	0.14	0.19	0.18	0.058	0.059	-	-	(0.014)	(0.004)	0.22	-	-
G 119	0.93	1.15	0.16	0.018	0.0064	0.064	0.049	0.042	-	0.006	(0.0007)	-	0.010	0.007	-	-	-

Ca N Ø 40x40 mm

- 0.0058 **Stahl, niedr. leg.**
 0.0003 0.0133 **Low Alloy Steel**
 - 0.0100
 - 0.0154
 (0.0002) 0.0142
 - 0.0087
 - 0.0130
 (0.0002) 0.0154
 (0.0002) 0.0120
 (0.0002) 0.0086

CRM C Mn Si P S Cr Ni Cu Mo V Al Ø 40x15 mm, wrought

G 51/1	0.40	1.53	0.29	0.023	(0.009)	0.62	0.15	0.45	1.50	(0.013)	-	Stahl, niedr. leg. Low Alloy Steel
G 52/1	0.41	0.25	1.38	0.012	(0.009)	0.12	2.35	0.094	(0.041)	-	-	
G 53/1	0.41	0.60	0.104	0.018	0.011	2.85	0.28	0.17	0.13	0.28	-	
G 54/1	0.43	0.14	0.17	(0.009)	0.010	0.12	4.01	(0.034)	(0.007)	0.19	-	
G 55/1	0.44	0.43	0.79	0.017	(0.009)	1.02	0.60	0.12	0.27	0.52	-	
G 56/1	0.41	0.25	1.69	0.011	0.007	0.43	0.69	0.41	0.66	0.19	-	
G 57/1	0.46	1.05	0.58	0.028	0.012	1.67	0.15	0.14	0.48	0.34	-	
G 58/1	0.40	1.81	0.35	0.026	0.012	0.20	1.44	0.31	0.21	0.079	-	
G 63/2	0.40	0.63	0.16	0.017	0.009	0.16	0.13	0.14	-	-	(0.010)	
G 64/2	0.75	0.47	0.22	0.012	(0.005)	0.090	0.081	0.12	-	-	0.020	
G 65/2	1.19	0.27	0.13	0.013	0.007	0.079	0.067	0.059	-	-	0.030	
G 66/2	(0.041)	0.095	(0.028)	0.008	0.006	0.011	0.017	0.028	(0.002)	(0.004)	(0.073)	

CRM C Mn Si P S Cr Ni Cu Mo V Al Ø 40x15 mm, wrought

G 101/2	0.033	1.97	-	0.010	0.007	0.035	2.06	0.46	0.010	0.30	0.036	Stahl, niedrig leg. Low Alloy Steel
G 102/3	1.11	0.15	1.06	0.014	-	1.59	0.021	0.13	0.43	-	0.017	

CRM C Mn Si P S Cr Ni Cu Mo V Al Ø 32x28 mm

GB 01223	0.095	0.238	0.053	0.010	0.052	0.142	0.316	0.050	0.040	(0.0004)	0.0089	0.071	Kohlenstoffstahl mit B nur Satz/set only
GB 01224	0.167	0.362	0.293	0.010	0.038	0.172	0.299	0.097	0.076	0.0031	0.156	0.071	Carbon Steel with B
GB 01225	0.292	0.460	0.469	0.030	0.028	0.211	0.250	0.147	0.016	0.0018	0.510	0.104	
GB 01226	0.423	0.562	0.272	0.032	0.018	0.26	0.196	0.084	0.017	0.0031	0.602	0.154	
GB 01227	0.493	0.663	0.573	0.062	0.063	0.370	0.112	0.123	0.010	0.0014	0.504	0.204	
GB 01228	0.048	0.179	0.098	0.029	0.0097	0.392	0.443	0.026	0.086	0.0069	0.492	0.069	

CRM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	V	Nb	Ti	Sn	As	N	Ø 35x20mm
IP 500	0.106	0.844	0.016	0.0048	0.282	0.270	0.018	0.612	0.0013	0.046	0.0046	0.003	0.008	0.0014	0.002	0.002	0.0092	Stahl, niedr.leg.
IP 501	0.277	0.723	0.016	0.030	0.208	0.083	0.063	1.05	0.210	0.034	0.008	-	-	0.0015	0.008	-	0.0076	niedr.leg.
IP 502	0.210	0.823	0.010	0.026	0.198	0.121	0.408	0.485	0.155	0.024	0.0083	-	-	0.0016	-	-	0.0069	LA-Steel
CRM	C	P	S	Cr	Mo	Ø 30-42x15 mm, wrought												
J 24	0.1744	0.0151	0.0010	1.048	0.578	Kohlenstoffstahl; Carbon Steel												
J 24 Späne lieferbar; Chips available																		
RM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Co	Sn	Al	W	V	Ti	As	Ø 40x15 mm, cast	
4 12746T	0.032	0.16	0.08	0.068	1.93	0.21	0.23	0.61	0.50	0.11	0.25	0.01	0.12	0.01	0.05	0.075	Kohlenstoffstahl	
4 12747U	0.155	0.33	0.040	0.030	2.00	0.385	0.45	0.50	0.44	0.20	0.16	0.01	0.03	0.037	0.07	0.02	Carbon Steel	
4 12748T	0.135	0.122	0.052	0.053	0.494	0.454	0.755	0.300	0.543	0.280	0.074	0.009	0.056	0.0464	(0.003)	0.1045		
4 12749V	0.138	0.549	0.080	0.036	1.531	0.609	0.549	0.224	0.269	0.484	0.0240	0.026	0.035	0.0419	0.0361	0.074		
4 12750S	0.202	0.57	0.058	0.022	0.54	0.70	0.70	0.11	0.11	0.61	0.22	0.27	-	-	0.11	0.12		
RM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Co	Sn	Al	W	V	Ti	As	Ø 40x15 mm, wrought	
4 349B	0.278	0.295	0.0326	0.0340	0.910	0.285	0.190	0.058	0.308	0.0211	0.175	0.152	0.053	0.125	0.0158	0.0050	C-Stahl; C-Steel	
RM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	Ti	V	W	As	Co	Nb	Bi
4 352C	0.257	0.498	0.131	0.074	0.533	0.380	0.348	0.242	0.162	0.124	0.090	0.246	0.042	0.140	0.030	0.031	-	-
4 353C	0.194	0.142	0.025	0.0205	0.817	0.190	0.491	0.113	0.302	0.057	0.0070	0.057	0.0481	0.108	0.056	0.057	0.096	0.021
	Se	Sb	Zn	Ø 42x15 mm, wrought														
	-	-	-	C-Stahl														
	0.017	0.156	0.048	C-Steel														
RM	C	Si	S	P	Mn	Al	V	Co	Sb	B	Nb	Zr	Ø 38x15-20 mm, wrought					
4 354A	0.27	0.19	0.015	0.066	0.86	0.01	0.02	0.03	0.05	(0.002)	0.07	0.03	Kohlenstoffstahl					
4 355A	0.20	0.48	0.024	0.028	0.62	<0.01	0.11	0.05	0.08	0.001	0.02	<0.01	Carbon Steel					
4 356A	0.36	0.37	0.032	0.049	0.44	0.05	0.09	0.12	0.02	0.007	0.02	0.01						
4 357A	0.45	0.23	0.062	0.016	0.24	0.06	0.19	0.21	<0.005	0.014	<0.001	<0.005						

RM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Co	Sn	Al	V	N	W		
4 15217P	0.52	1.47	0.069	0.072	0.97	0.57	1.04	0.30	0.19	0.195	0.05	0.04	0.78	-	-		
4 15251T	1.17	2.27	0.0258	0.0284	1.003	1.025	0.792	0.205	0.110	0.259	0.0047	0.050	0.405	0.232	0.053		
4 15252P	0.094	0.26	0.054	0.082	1.03	2.00	0.75	0.246	0.17	0.15	0.05	0.03	0.35	-	-		
4 15253R	0.240	0.37	0.054	0.072	1.14	0.515	1.49	0.525	0.41	0.088	0.19	0.19	0.250	0.043	0.34		
4 15255P	0.47	1.10	0.021	0.112	1.16	0.388	1.98	0.110	0.38	0.048	0.095	0.12	0.54	0.021	0.21		
4 15256N	0.09	0.16	0.042	0.046	1.51	3.51	0.32	0.07	0.06	0.28	0.15	0.03	0.64	-	-		
4 15259N	0.67	1.83	0.110	0.043	0.31	3.97	0.47	0.42	0.54	0.110	0.089	0.26	0.40	0.005	1.04		
4 15260V	0.446	0.456	0.094	0.031	2.20	0.573	3.69	0.130	0.231	0.109	0.0130	0.378	0.351	-	-		
4 15266T	0.454	0.667	0.0093	0.079	1.45	1.50	2.78	0.365	0.253	0.235	0.0160	0.453	0.089	-	-		
Nb As Ta Pb B 40-42x15 mm, cast																	
-	-	-	-	-	-	Stahl, niedr. leg											
0.29	-	-	-	-	-	Low Alloy Steel wrought											
-	-	-	-	-	-	wrought											
0.51	-	-	-	-	-	wrought											
0.16	-	-	-	-	-	wrought											
-	-	-	-	-	-												
0.06	0.051	(0.042)	0.007	0.011	-	chill cast											
0.243	0.087	0.026	-	-	-	chill cast											
1.481	0.063	0.20	-	-	-	chill cast											
RM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Al	V	W	Co	N	Ø 40x15 mm, wrought		
4 LA1A	0.06	0.73	0.045	0.013	1.32	0.21	0.95	<0.01	0.034	<0.01	0.41	-	-	-	Stahl, niedr. leg.		
4 LA2C	0.18	1.02	0.043	0.027	0.43	0.785	0.760	0.175	0.37	1.63	0.069	-	0.0495	0.012	Low Alloy Steel		
4 LA3A	0.48	0.13	0.040	0.032	1.50	0.31	0.37	0.30	0.20	0.06	0.19	-	-	0.006			
4 LA4B	0.537	0.335	0.039	0.0363	0.303	0.521	0.499	0.489	0.334	0.057	0.328	0.091	0.105	0.0222			
4 LA5A	0.81	0.67	0.015	0.057	0.98	0.13	0.12	0.19	0.09	0.19	0.58	0.51	-	-			
4 LA6A	0.01	0.06	0.006	0.005	0.10	0.03	0.03	<0.01	0.01	<0.01	<0.01	0.20	-	-			
RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	N	As	Co	Ca	Sn	V	Ø 35-44x19 mm
6 XCCT	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.020	0.006	0.0076	0.004	0.017	-	0.002	0.031	-
6 51E	0.15	0.59	0.010	0.021	0.28	0.22	1.75	0.14	0.21	0.028	0.0086	-	0.035	-	0.010	(0.0011)	AISI 4615
6 60C	0.42	0.80	0.011	0.013	0.24	0.15	1.71	0.87	0.25	0.034	0.0067	-	0.012	-	0.009	<0.004	AISI 4340
6 60D	0.406	0.82	0.014	0.009	0.22	0.075	1.76	0.76	0.23	0.032	0.0070	(0.004)	0.011	(0.0005)	0.004	0.010	AISI 4340
6 60E	0.408	0.70	0.012	0.024	0.26	0.153	1.73	0.86	0.249	0.024	0.0087	0.007	0.009	0.0010	0.09	0.004	AISI 4340
6 4340M	0.414	0.74	0.004	<0.001	1.65	0.134	1.78	0.78	0.35	0.076	0.0020	0.007	0.013	-	0.009	0.056	AISI 300M
6 69B	0.26	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.39	(0.024)	0.0057	-	0.035	-	0.006	0.002	AISI AMS6418
6 3961	0.215	0.565	0.016	0.022	0.236	0.133	1.67	0.510	0.27	0.022	0.0079	-	(0.010)	-	(0.008)	(0.002)	AISI E4320
6 3962	0.168	0.58	0.007	0.018	0.244	0.146	1.83	0.138	0.219	0.023	0.0072	0.005	0.007	-	0.007	(0.001)	AISI 4617

RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	N	As	Co	Ca	O	Sn	V	Ø 35-44x19 mm	
6 4330V	0.318	0.91	0.008	0.0009	0.240	0.181	1.91	0.91	0.475	0.021	0.0076	-	0.011	0.0010	0.0018	0.010	0.094	AISI 4330	
6 LF3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.056	0.017	0.0054	0.006	0.056	B=0.0001	0.004	0.006	(0.002)	AISI LF3	
6 4820	0.188	0.57	0.010	0.025	0.25	0.11	3.29	0.12	0.21	0.020	0.0079	0.005	0.008	0.0046	0.0027	(0.008)	(0.002)	AISI 4820	
6 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.31	0.030	0.0089	0.004	0.010	0.0049	0.0010	0.009	0.004	AISI 9325	
6 1972	0.130	0.51	0.012	0.017	0.24	0.089	3.28	1.53	0.052	0.014	0.0096	0.004	0.012	(0.0002)	(0.0026)	0.006	0.003	AISI 3310	
RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	O	Sn	V	Nb	
6 XCCS	0.042	0.32	0.003	0.014	0.010	0.018	0.017	0.014	0.005	0.069	0.002	-	0.003	0.0047	-	0.006	<0.002	-	
6 2931A	0.178	0.842	0.0046	0.0262	0.244	0.199	0.064	0.086	0.018	0.0011	0.005	0.0014	0.0067	0.0099	0.0050	0.0094	0.0006	(0.0004)	
6 57F	0.196	0.554	0.009	0.027	0.202	0.197	0.070	0.120	0.018	(0.002)	(0.006)	(0.0003)	(0.007)	0.0077	(0.006)	0.008	0.063	-	
6 2971	0.187	1.01	0.015	0.024	0.0237	0.065	0.111	0.152	0.040	0.022	0.003	-	-	0.0084	-	(0.005)	(0.002)	-	
6 4932	0.234	0.76	0.010	0.015	0.25	0.15	0.080	0.144	0.033	(0.001)	(0.005)	-	0.005	0.0080	0.0028	0.008	0.060	-	
6 4931	0.352	0.80	0.011	0.016	0.27	0.217	0.070	0.093	0.024	(0.001)	0.005	-	0.006	0.0080	0.0034	0.009	0.058	-	
6 3941	0.41	0.80	0.016	0.023	0.25	0.053	0.019	0.068	0.006	0.002	0.003	0.0013	0.004	0.0070	(0.006)	(0.002)	0.003	0.031	
6 3942	0.47	0.72	0.023	0.032	0.26	0.281	0.14	0.165	0.037	0.004	0.009	0.0012	0.010	(0.0088)	(0.0041)	0.012	0.0019	0.019	
6 4972	0.460	0.74	0.015	0.024	0.335	0.220	0.056	0.058	0.012	0.002	0.005	0.0013	0.007	0.0089	(0.009)	0.028	0.012	(<0.002)	
6 2972	0.462	0.70	0.011	0.016	0.204	0.270	0.129	0.119	0.021	(0.002)	0.008	-	-	0.0088	-	(0.026)	0.024	-	
6 64C	0.92	0.22	0.015	0.0024	0.22	0.016	0.038	0.26	0.008	(0.005)	-	-	0.004	0.0084	-	0.001	0.005	-	
Pb	Sb	Ti	B	Ø 35-44x19 mm, wrought															
-	-	-	-	AISI 1005	Stahl, niedr. leg.														
0.0008	0.0021	0.0006	0.0004	AISI 1018	Low Alloy Steel														
-	-	-	-	AISI 1020															
-	-	-	-	AISI LF2															
-	-	-	-	AISI 1026															
-	-	-	-	AISI 1035															
0.0010	-	-	-	AISI 1040															
0.0003	-	-	-	AISI 1045															
(0.001)	(<0.004)	0.0015	0.0002	AISI 1045															
-	-	(0.002)	-	AISI 1045															
-	-	-	-	AISI 1095															
RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	V	Al	As	B	Ca	Co	N	O	Nb	
6 CCS-2	0.200	0.885	0.046	0.040	0.310	0.096	0.314	0.269	0.100	0.080	0.038	0.016	0.0037	(0.0001)	0.055	(0.0006)	(0.0010)	0.049	
6 234	0.312	0.75	0.010	0.0018	0.26	0.049	1.68	0.64	0.10	0.009	0.007	0.001	0.0037	(<0.0005)	0.004	0.0013	0.0016	(0.001)	
6 3972	0.195	1.30	0.083	0.056	0.106	0.082	1.19	0.108	0.032	0.191	0.031	0.012	0.0104	-	0.010	0.0065	0.0038	(0.001)	
Sb	Sn	Ti	W	Zr	Pb	Ta	32-35x32-35x19 mm												
0.024	0.017	0.037	0.042	0.002	0.0032	0.020	CRM	38x38x30 mm											
(<0.002)	(<0.002)	0.0014	(<0.002)	(<0.003)	-	-	Stahl, niedr. leg												
-	0.012	0.163	(<0.008)	-	-	-	Low Alloy Steel												

RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	B	Bi	Ca	Ce	Co	Hg	
6 13B	0.211	0.316	0.018	0.005	0.015	0.023	0.43	0.081	0.050	0.016	0.050	(0.00002)	(<0.0001)	(<0.0001)	(<0.0005)	0.19	(<0.00001)	
6 15A	0.142	1.12	0.016	0.008	0.058	0.030	0.029	0.044	0.008	0.041	0.003	(0.0002)	-	(0.0005)	(0.003)	0.005	-	
	La	Mg	N	O	Nb	Pb	Sb	Se	Sn	Ta	Te	Ti	V	W	Zn	Zr	Ø 32x17 mm, ch.cast	
	(<0.0005)	(0.00005)	0.0099	(0.02)	0.003	0.0009	0.027	0.023	0.061	0.005	(0.00005)	0.004	0.010	0.04	0.0003	(0.01)	Stahl, niedr. leg.	
	-	-	-	-	0.041	(0.0003)	(0.003)	-	0.002	-	-	0.008	0.012	(0.004)	-	0.022	Low Alloy Steel	
RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Sn	V	N	O	Co	As	Sb	
6 3952	0.208	0.564	0.011	0.021	0.264	0.202	0.112	0.105	0.519	0.048	-	-	(0.0005)	-	-	-	-	
6 1981	0.143	0.49	0.0090	0.017	0.66	0.154	0.132	1.19	0.472	0.023	0.007	0.005	0.0089	0.0024	0.0094	-	-	
6 45A	0.133	0.46	0.016	0.022	0.69	0.17	0.15	1.16	0.52	0.032	0.011	0.004	0.0081	0.0025	0.009	0.007	0.0027	
6 46A	0.139	0.55	0.018	0.030	0.18	0.13	0.20	2.37	0.93	0.022	0.008	0.013	0.0140	(0.0038)	0.011	-	-	
6 1982	0.126	0.44	0.013	0.026	0.25	0.18	0.20	2.07	0.88	0.023	0.013	0.005	0.0100	0.0020	0.0106	-	0.002	
6 47A	0.130	0.44	0.017	0.015	0.27	0.11	0.12	4.22	0.47	0.015	0.008	0.016	0.0181	(0.003)	0.011	-	-	
6 47B	0.122	0.39	0.014	0.022	0.22	0.12	0.105	4.78	0.45	0.018	0.006	0.004	0.023	(0.004)	-	0.004	(0.002)	
6 48A	0.121	0.43	0.012	0.011	0.68	0.13	0.29	8.75	0.95	0.018	0.014	0.014	0.021	-	0.022	-	-	
6 9905	0.107	0.333	0.008	0.008	0.327	0.115	0.123	8.22	0.90	0.017	0.009	0.236	0.055	0.0021	0.016	0.007	(0.002)	
	Ti	Nb	B	W	Ø 38x19 mm, wrought													
	-	-	-	-	-													
	-	-	0.003	-	F-11													
	-	-	-	-	F-11													
	-	-	-	-	F-22													
	-	-	0.0002	-	F-22													
	0.003	0.002	-	-	F-5													
	(0.003)	(<0.004)	-	(<0.002)	F-5													
	0.002	-	-	-	F-9													
	(0.002)	0.076	(0.0004)	0.003	F-91	CRM												
RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Bi	As	Ca	Co	N	O	Pb	Se
6 4140A	0.40	0.84	0.021	0.076	0.21	0.15	0.15	0.97	0.16	0.016	0.105	0.005	(0.0003)	0.010	0.0098	(0.0025)	(0.001)	-
6 4140B	0.43	0.76	0.027	0.037	0.20	0.006	0.012	0.84	0.16	0.036	0.087	(0.002)	(0.0002)	0.005	0.0064	(0.002)	0.004	-
6 4150MOD	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.21	0.012	0.070	0.005	0.0010	0.012	0.0087	(0.003)	0.0010	-
6 8620A	0.184	0.80	0.008	0.079	0.21	0.15	0.44	0.48	0.16	0.016	0.073	0.007	0.0003	0.010	0.0107	(0.004)	(0.001)	-
6 8620B	0.202	0.84	0.014	0.029	0.23	0.135	0.44	0.59	0.17	0.022	0.105	0.005	0.0009	0.011	0.0100	0.003	(0.002)	-
6 53MOD	1.01	0.36	0.011	0.012	0.26	0.070	0.072	1.37	0.024	0.019	0.102	0.004	(0.001)	0.007	0.0086	(0.002)	0.0005	-
6 4142SE	0.428	0.85	0.015	0.031	0.17	0.13	0.081	0.84	0.164	0.017	-	0.16	-	0.012	0.0087	(0.002)	0.0020	0.042
	Sn	Ti	V	Ø 38x12 mm, wrought														
	0.011	(0.003)	0.004	AISI 4140 + Bi + S														
	(0.002)	0.003	0.005	AISI 4140 + Bi														
	0.013	(0.002)	0.008	AISI 4150 + Bi + S														
	0.009	(0.002)	0.004	AISI 8620 + Bi + S														
	0.009	(0.002)	0.003	AISI 8620 + Bi														
	0.008	-	0.005	AISI E52100 + Bi														
	0.015	(0.002)	0.003	AISI 4142 + Se														

RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	W	Co	V	Al	Sn	Pb	N	O	As
IA 27D	0.002	0.001	0.001	0.001	0.003	0.001	0.003	0.002	0.001	0.002	0.004	<0.0005	0.001	0.001	<0.0005	0.001	0.01	0.001
IA 28H	0.175	0.82	0.015	0.031	0.26	0.120	0.070	0.129	0.034	0.003	0.0051	0.0015	0.027	0.0059	<0.001	0.0076	0.0015	0.0071
IA 209C	0.31	0.70	0.008	0.024	0.233	0.21	0.071	0.117	0.016	0.004	0.007	0.032	0.003	0.017	0.001	0.0123	0.004	0.007
IA 210C	0.443	0.87	0.033	0.025	0.219	0.36	0.097	0.161	0.017	<0.005	0.008	0.005	0.005	0.019	0.002	0.0090	0.009	0.008
IA 200B	0.452	0.755	0.013	0.026	0.219	0.228	0.089	0.132	0.018	0.002	0.007	0.024	0.003	0.009	0.0004	0.0097	0.004	0.005
IA 254A	0.500	0.78	0.010	0.024	0.211	0.091	0.044	0.050	0.013	(0.001)	0.006	0.002	0.025	0.005	(0.0003)	0.0096	(0.003)	0.005
IA 29C	0.18	1.20	0.011	0.13	0.28	0.15	0.075	0.076	0.016	(0.002)	(0.01)	0.003	0.003	0.008	<0.001	0.010	0.005	0.009
IA 199B	0.45	1.45	0.009	0.29	0.18	0.089	0.035	0.048	0.008	-	0.007	0.003	0.003	0.005	(<0.01)	0.0059	(0.0048)	0.005
IA 206A	0.068	0.90	0.069	0.26	(0.019)	0.098	0.044	0.041	0.012	-	0.009	0.002	0.004	0.005	-	0.0119	(0.019)	0.008
IA 143C	0.297	0.56	0.006	0.011	0.21	0.22	0.155	0.95	0.22	0.002	0.011	0.003	0.038	0.020	(0.001)	0.0089	0.0014	0.008
IA 30F	0.407	0.79	0.013	0.018	0.24	0.033	0.023	1.02	0.204	0.002	0.005	0.004	0.026	0.007	0.001	0.0045	0.003	0.005
IA 31C	0.41	0.71	0.013	0.022	0.25	0.23	1.81	0.87	0.26	(0.01)	0.010	0.006	0.027	0.010	(<0.01)	0.0081	0.0008	-
IA 33D	0.209	0.593	0.009	0.023	0.207	0.072	1.78	0.139	0.229	<0.005	0.008	0.002	0.026	0.005	<0.01	0.0053	0.0013	0.0035
IA 49C	1.04	0.31	0.009	0.013	0.26	0.082	0.064	1.35	0.015	(<0.005)	0.007	0.008	0.016	0.005	(<0.001)	0.0078	(0.0012)	0.004
IA 34B	0.48	0.81	0.021	0.021	0.29	0.21	0.14	0.94	0.053	(<0.01)	0.009	0.16	0.024	0.012	(<0.01)	0.0089	0.0018	-
IA 32C	0.188	0.81	0.009	0.024	0.220	0.119	0.447	0.49	0.169	0.004	0.006	0.003	0.026	0.006	(0.001)	0.0081	0.0018	0.004
IA 182B	0.21	0.81	0.016	0.037	0.27	0.017	0.48	0.49	0.172	0.006	0.006	0.004	0.038	0.0019	0.19	0.0040	0.003	0.003
IA 252C	0.416	0.92	0.025	0.008	0.248	0.109	0.505	0.501	0.205	<0.005	0.008	0.005	0.017	0.007	0.001	0.0083	(0.002)	0.004
IA 213A	0.16	0.66	0.015	0.034	0.15	0.41	0.15	0.15	0.048	(0.007)	0.008	0.002	0.0018	0.004	0.0025	0.0082	0.011	0.007
IA 35F	0.126	0.50	0.009	0.020	0.57	0.030	0.047	1.16	0.48	0.004	0.004	0.004	0.036	0.002	<0.003	0.0060	0.0016	<0.01
IA 229A	0.218	0.86	0.008	0.010	0.331	0.014	0.029	0.015	0.493	(0.003)	0.011	0.006	0.027	0.002	(0.001)	0.0071	0.0013	(0.002)
IA 36B	0.14	0.49	0.01	0.038	0.21	0.13	0.18	2.18	0.95	(<0.01)	0.012	0.006	0.03	0.008	(0.003)	0.0102	0.0018	-
IA 37B	0.119	0.431	0.011	0.016	0.235	0.137	0.11	4.82	0.470	0.013	0.017	0.012	0.025	0.008	(0.0003)	0.0155	0.0024	0.006
IA 38B	0.13	0.41	0.008	0.018	0.38	0.15	0.24	8.67	0.96	(0.02)	0.029	0.02	0.009	0.014	-	(0.02)	0.019	-

Ti **Nb** **B** **Zr** **Ca** Ø 31x18.75 mm + Ø 31x5 mm

0.001 0.001 <0.001 - - Iron Electrolytic Stahl, unleg./niedr. leg.
 0.0059 0.0015 0.0002 0.001 0.0005 AISI 1018 Carbon/Low Alloy Steel
 0.0018 0.0018 0.0002 - 0.001 AISI 1030

0.001 0.025 0.003 - - AISI 1040 IA 27D-38B auch als Satz lieferbar: IA CLA20/IA CLA27
 0.002 0.001 0.0001 0.0010 0.0012 AISI 1045 also available as set

Master-Satz von 100 Proben auf Anfrage
 Master Set of 100 pieces on request

0.001 0.001 0.0002 (0.001) 0.001 AISI 1050
 0.0015 (0.003) (0.003) - - AISI 1117
 0.002 (0.002) 0.002 - - AISI 1144
 0.0015 (0.002) 0.0006 - - AISI 1215
 0.002 0.002 0.0002 - - AISI 4130
 0.002 0.0014 0.0002 (0.001) (0.0003) AISI 4140 IA 27D(C)-38B(C) Späne lieferbar 100 g Flaschen
 0.003 0.002 0.0002 - - AISI 4340 Chips available 100 g bottles
 0.003 0.002 0.0002 <0.002 (0.0003) AISI 4620
 0.003 0.001 (0.0001) - - AISI E52100
 0.002 0.002 0.0002 - - AISI E6150
 0.002 0.002 0.0001 (0.001) 0.0008 AISI 8620
 0.003 0.003 0.0003 0.0013 (0.0005) AISI 86L20
 0.001 0.002 (0.0001) <0.002 (0.0003) AISI 8740
 0.001 0.002 0.0003 - - A36
 0.0027 0.003 0.0003 0.0012 - 1-1/4Cr-1/2Mo
 0.002 0.002 0.0002 - - C1/2 Mo, F1
 0.003 0.004 (0.0003) - - 2-1/4Cr-1Mo
 0.0021 0.005 0.0002 0.002 (0.0004) 5Cr-1/2Mo
 0.003 0.008 (0.0004) - - 9Cr-1Mo

CRM	C	S	P	Si	Mn	Cr	Ni	Cu	Ti	W	Fe	Ø 30x18 mm, cast			
2 H2	0.42	(0.003)	0.020	0.42	0.91	15.0	0.31	0.35	(0.05)	0.50	(82.0)	Stahl, warmfest			
2 H5	0.12	(0.003)	0.017	0.70	0.48	21.8	0.20	0.22	0.03	0.10	(76.3)	SS-Steel, heat resistant			
2 H6	0.20	0.024	0.021	0.67	0.49	18.9	0.15	0.10	0.10	(0.12)	(79.3)				
2 H7	0.062	0.022	0.018	0.42	0.35	9.07	0.10	0.085	0.21	0.15	(89.0)				
CRM	C	S	P	Si	Mn	Cr	Cu	Al	Ø 30x20 mm, cast						
2 K8	0.061	0.017	0.026	1.38	1.10	23.5	(0.18)	1.53	Stahl, warmfest;	Steel, heat resistant					
CRM	C	Mn	P	S	Si	Cu	Ni	Cr	V	Mo	N	Ø 31x19 mm, wrought			
3 1219	0.149	0.42	0.026	0.001	0.545	0.162	2.16	15.64	0.056	0.164	0.078	AISI 431 Edelstahl, niedr. Ni			
3 1223	0.127	1.08	0.018	0.329	0.327	0.081	0.232	12.64	0.068	0.053	(0.05)	AISI 416 Stainless Steel, low Ni			
												3 1219 Späne lieferbar Chips available			
CRM	C	Si	Mn	P	S	Cr	Mo	Ni	Co	Cu	V	Ø 38x19 mm, wrought			
5 469	0.279	0.421	0.598	0.015	0.020	11.93	-	0.246	(0.01)	(0.02)	(0.02)	Edelstahl, niedr. Ni			
5 470	0.153	0.335	0.235	0.024	0.035	17.68	-	0.369	(0.02)	(0.02)	(0.02)	Stainless Steel, low Ni			
5 471	0.095	0.326	0.417	0.018	0.023	23.85	-	0.96	(0.02)	(0.02)	(0.03)				
5 472	0.227	1.05	1.02	0.032	0.029	15.82	0.661	1.95	(0.02)	(0.02)	(0.02)				
5 473	0.172	0.604	0.494	0.019	0.030	9.06	0.95	(0.06)	(0.01)	(0.02)	(0.02)				
CRM	C	Si	Mn	P	S	Cr	Ni	Ø 44x13 mm, wrought							
5 70	0.18	0.35	0.38	0.024	0.020	16.35	0.40	Edelstahl, niedr. Ni;	Stainless Steel, low Ni						
CRM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Co	Ti	Ø 32x30 mm, wrought			
CI 15701-1	0.057	0.362	0.048	0.008	0.344	0.028	0.293	15.66	0.085	0.238	0.0062	Edelstahl, niedr. Ni			
CI 15701-2	0.174	0.505	0.034	0.008	0.541	0.075	0.351	13.61	0.171	0.181	0.0065	Stainless Steel, low Ni			
CI 15701-3	0.261	0.648	0.028	0.069	0.748	0.188	0.090	11.91	0.367	0.291	0.0064				
CI 15701-4	0.366	0.151	0.024	0.024	0.936	0.230	0.188	8.75	0.359	0.138	0.0074	nur Satz/set only			
CI 15701-5	0.502	1.17	0.016	0.042	1.38	0.263	0.240	7.85	0.460	0.103	0.0068				
CRM	C	Mn	P	S	Si	Cu	Ni	Cr	V	Mo	W	Co	Ti	Al	Ø 35x58 mm, wrought
CM 2141	0.132	0.53	0.0035	0.014	0.23	(0.033)	0.21	14.35	(<0.001)	(<0.001)	(0.012)	(0.010)	(0.004)	(0.005)	Edelstahl, niedr. Ni
CM 2142	0.253	0.26	0.016	0.004	0.635	(0.090)	0.51	13.54	(0.001)	(0.016)	(0.016)	(0.016)	(0.008)	(0.010)	Stainless Steel, low Ni
CM 2143	0.50	0.40	0.029	0.0125	0.50	(0.095)	0.42	12.45	(<0.001)	(0.015)	(0.016)	(0.015)	(0.10)	(0.013)	
CM 2144	0.051	0.065	0.010	0.021	0.03	(0.089)	0.04	15.35	(0.003)	(0.015)	(0.013)	(0.014)	(0.002)	(0.002)	nur Satz/set only
CM 2145	0.33	0.67	0.035	0.011	0.73	(0.094)	0.69	11.48	(0.001)	(0.015)	(0.0159)	(0.014)	(0.010)	(0.017)	
CRM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	W	V	Ti	Co	Ø 33x33 mm, wrought	
CM 2164	0.040	0.130	0.0062	0.0028	0.223	0.056	0.500	14.26	0.064	0.058	0.059	0.041	0.016	Edelstahl, niedr. Ni	
CM 2165	0.245	0.337	0.0103	0.032	0.420	0.284	0.393	11.03	0.353	0.27	0.151	0.079	0.054	Stainless Steel, low Ni	
CM 2166	0.159	0.495	0.0165	0.017	0.568	0.171	0.207	12.52	0.157	0.19	0.089	0.091	0.036		
CM 2167	0.340	0.740	0.0262	0.0054	0.772	0.374	0.461	9.37	0.244	0.38	0.201	0.371	0.078	nur Satz/set only	
CM 2168	0.472	0.983	0.043	0.041	0.487	0.522	0.771	7.84	0.487	0.50	0.287	0.187	0.116		

RM	Al	B	C	Co	Cr	Cu	Mn	Mo	N	Nb	Ni	O	P	S	Si	Sn
IA 9C	0.014	(0.0003)	0.122	0.038	12.04	0.063	0.38	0.192	0.019	0.005	0.33	0.0039	0.021	0.029	0.35	0.002
IA 10C	0.003	<0.0005	0.128	0.022	12.25	0.155	0.35	0.08	0.015	0.003	0.24	0.008	0.026	0.29	0.37	0.009
IA 154B	0.002	(0.001)	0.35	0.020	12.20	0.087	0.405	0.079	0.020	0.003	0.223	0.0016	0.017	0.0004	0.45	0.006
IA 205B	0.009	0.0003	0.220	0.025	11.72	0.149	0.68	0.97	0.049	0.018	0.702	0.0016	0.014	0.001	0.37	0.006
IA 11C	0.010	<0.0005	0.055	0.017	17.66	0.070	0.52	0.055	0.029	0.005	0.219	0.004	0.018	0.0030	0.51	0.01
IA 12B	(0.003)	(0.0003)	0.174	0.018	16.02	0.143	0.6	0.057	0.061	0.011	2.15	0.0101	0.016	0.003	0.56	0.006
IA 13C	0.003	<0.0005	1.02	0.021	16.84	0.031	0.43	0.455	0.0188	0.004	0.108	0.0029	0.017	0.001	0.69	(0.004)
IA 14B	0.004	(0.0004)	0.016	0.030	23.60	0.071	0.426	0.095	0.043	0.006	0.29	0.0054	0.022	0.0015	0.51	0.005
IA 20C	(0.004)	-	0.18	0.031	12.15	0.060	0.30	0.12	0.0222	0.010	1.93	0.0068	0.018	0.007	0.35	0.004
<hr/>																
Ti	V	W	Zr	As	Ø 31x18.5 mm + 31x5 mm											
0.002	0.080	0.073	(0.001)	-	AISI 410	Edelstahl, niedr. Ni										
0.002	0.024	0.011	(0.001)	-	AISI 416	Stainless Steel, low Ni										
0.002	0.067	0.010	-	-	AISI 420											
0.003	0.262	1.1	-	0.005	AISI 422											
<0.003	0.031	<0.005	<0.005	-	AISI 430											
0.003	0.037	0.014	-	-	AISI 431											
0.005	0.10	<0.005	<0.002	-	AISI 440C	IA 9C(C) - 20C(C) Späne lieferbar 100 g										
0.006	0.058	0.0020	-	-	AISI 446	Chips available										
(0.003)	0.086	2.59	-	-	Greek Ascoloy											

Manganstähle, Automatenstähle mit Pb + S, Dynamostähle und Nitrierstähle, siehe unter Abschnitt 2.5. Spezialstahl

Manganese Steels, Free Cutting Steels, Resulphurized Steels, Dynamo Steels and Cementation Steels, see part 2.5. Special Steel

CRM	C	S	P	Si	Mn	Cr	Ni	Cu	Mo	Ti	Nb	Fe	Ø 30x20 mm, cast
2 S5	0.21	0.003	0.032	0.87	(1.90)	20.2	14.8	0.45	0.20	0.13	-	(61.0)	Edelstahl, aust.
2 S15	0.043	0.013	(0.02)	0.26	0.38	16.7	3.90	1.54	2.64	-	0.64	(74.0)	Stainless Steel, aust.

CRM	C	Si	Mn	S	P	Cu	Ni	Cr	Ti	Mo	Nb	Fe	Ø 35x20 mm, cast
2 S19	0.26	2.32	0.32	0.021	0.012	0.19	12.8	7.00	0.048	0.11	0.81	(76.1)	Edelstahl, aust.
2 S20	0.097	1.80	1.50	0.025	0.011	0.44	18.2	2.06	(0.01)	3.15	1.22	(71.5)	Stainless Steel, aust.
2 S21	0.37	1.26	0.19	0.021	0.017	0.11	22.3	3.99	0.50	4.12	-	(67.1)	
2 S22	0.014	0.61	0.34	0.008	0.009	(0.02)	28.2	1.00	0.13	0.82	-	(68.8)	
2 S24	0.65	0.76	0.94	0.036	0.062	0.12	9.19	10.28	0.27	0.41	1.65	(75.6)	
2 S25	0.067	1.49	1.90	0.015	0.045	0.07	13.8	15.6	0.46	1.77	0.07	(64.7)	
2 S26	0.076	0.67	0.99	0.026	0.027	0.14	3.31	18.9	0.11	2.59	0.07	(73.1)	

CRM	C	S	P	Si	Mn	Cr	Ni	Cu	Mo	Nb	Ti	Ø 35x20 mm, cast
2 K7	0.063	0.012	0.026	0.89	1.44	17.8	10.45	0.20	-	-	0.27	Edelstahl, aust.
2 K10/C	0.13	0.020	0.022	0.88	1.77	17.5	11.2	0.16	2.98	0.98	-	Stainless Steel, aust.

CRM	C	Mn	P	S	Si	Cu	Ni	Cr	V	Mo	Co	Pb	Ø 31x19 mm, chill cast
3 C1151a	0.034	2.37	0.017	0.038	0.29	0.385	7.25	22.59	0.040	0.79	0.033	0.0039	Edelstahl, aust.
3 C1153a	0.225	0.544	0.030	0.019	1.00	0.226	8.76	16.70	0.176	0.24	0.127	0.006	Stainless Steel, aust.
3 C1154a	0.100	1.44	0.06	0.051	0.53	0.44	13.08	19.31	0.135	0.068	0.38	0.017	

CRM	C	Mn	P	S	Si	Cu	Ni	Cr	V	Mo	Co	Ti	Nb	Ta	Pb	Ø 31x19 mm	
3 1155	0.0445	1.619	0.0200	0.0175	0.5093	0.175	12.35	18.37	0.050	2.26	0.109	-	-	(0.001)	AISI 316	Edelstahl, aust.	
3 1171	0.067	1.81	(0.019)	(0.013)	0.536	0.1205	11.18	17.50	-	0.167	0.097	0.346	-	-	AISI 321	Stainless Steel,	
3 1172	0.056	1.76	0.025	0.014	0.59	0.105	11.35	17.40	-	0.22	0.12	-	0.65	<0.001	-	AISI 348	aust.

3 1155, 1171 + 1172 Späne lieferbar; Chips available

B R E I T L Ä N D E R G M B H

2.3.2

Edelstahl, aust.

Edelstahl, hoch leg.

(Stainless Steel, aust.)

(Stainless Steel, high alloy)

CRM C Mn P S Si Cu Ni Cr Mo Co Nb W B V Ø 31x19mm, chill cast

3 C2400 0.036 0.71 0.013 0.003 0.61 2.63 4.07 17.06 0.23 0.10 0.15 (0.1) (0.0004) 0.092 ACI-CD-4M-CU Edelstahl, hoch leg.
 3 C2401 0.062 1.03 0.025 0.027 0.74 3.17 5.46 25.1 2.13 0.19 (0.002) (0.18) (0.0004) 0.20 17-4PH Stainless Steel,

CRM C Mn P S Si Cu Ni Cr V Mo Co Fe Ø 31x19mm

3 1158 0.025 0.468 0.004 0.005 0.194 0.039 36.03 0.062 0.001 0.010 0.008 - Ni36 Edelstahl, aust.
 3 1159 0.007 0.305 0.003 0.003 0.32 0.038 48.2 0.06 - 0.010 0.022 51.0 Ni48Fe51 Stainless Steel, aust.

3 1158 + 1159 Späne lieferbar; Chips available

CRM C Si Mn P S Cr Mo Ni Al As Co Cu Nb Pb Sn Ti

5 461/1 0.0103 0.374 0.686 0.0053 0.0051 14.727 0.0138 6.124 (0.002) (0.004) - 0.0091 - - - -
 5 462/1 0.0345 0.463 0.722 0.0053 0.0041 11.888 0.0304 12.85 - - 0.0112 - - - -
 5 463/1 0.019 0.270 1.400 0.025 0.019 18.46 0.265 10.20 - - 0.116 0.276 - - - -
 5 464/1 0.086 0.57 0.791 0.020 0.028 25.39 - 20.05 - (0.003) 0.054 - - 0.0004 - -
 5 465/1 0.066 0.405 1.380 0.021 0.012 17.31 0.092 9.24 0.026 - 0.053 0.098 - - 0.40
 5 466/2 0.0141 0.480 1.311 0.0105 0.0069 17.84 2.776 10.20 (0.002) 0.0020 0.0184 0.0278 (0.001) (<0.001) (<0.001) (<0.002)
 5 467/1 0.082 0.52 0.788 0.018 0.019 18.09 - 9.21 - 0.004 - - 0.99 0.004 - -
 5 468/1 0.143 1.41 1.70 0.014 0.020 17.96 - 8.90 - - 0.018 - - - - -

V Ta B N Ø 38x19 mm, wrought

- - - - Edelstahl. aust.
 - - - - Stainless Steel, aust.
 - - 0.0022 0.063
 - - - -
 0.102 - 0.0006 0.010
 0.0346 - 0.0039 0.0508
 - 0.0017 - -
 - - - -

5 461/1-468/1 Späne lieferbar; Chips available

CRM C Si Mn P S Cr Mo Ni Al As Co Cu Nb Sn V Ø 38x19 mm, wrought

5 474 0.022 0.17 1.70 0.008 0.020 19.06 3.55 14.74 (0.006) 0.030 (0.02) 0.35 - - 0.30 Edelstahl, aust.
 5 475 0.050 0.21 0.89 0.037 0.008 14.14 1.59 5.66 0.013 - 0.22 1.94 0.22 0.015 - Stainless Steel, aust.

5 474 + 475 Späne lieferbar; Chips available

CRM C Si Mn P S Ni Cr Mo Cu Co Nb N Ø 35x30mm, wrought

9 650 0.053 0.30 0.48 0.024 0.0048 0.18 16.70 0.013 0.020 0.017 - 0.084 Edelstahl, aust.
 9 651 0.018 0.42 1.81 0.026 0.0027 10.20 18.42 0.24 0.16 0.13 - 0.0507 Stainless Steel, aust.
 9 652 0.044 0.42 1.73 0.031 0.0027 11.38 16.56 2.13 0.20 0.18 - 0.0084
 9 653 0.044 0.40 1.80 0.033 0.0006 13.96 22.43 0.20 0.16 0.20 - 0.0554 9 651, 653, 654 + 655 Späne lieferbar
 9 654 0.046 0.40 1.69 0.026 0.0006 19.42 24.79 0.23 0.15 0.15 - 0.0200 Chips available
 9 655 0.036 0.62 1.81 0.028 0.0043 9.52 17.34 0.22 0.20 0.17 0.55 0.0101 nur Satz/set only

B R E I T L Ä N D E R G M B H

Edelstahl, aust.
Edelstahl, hoch leg.

(Stainless Steel, aust.)
(Stainless Steel, high alloy)

2.3.5

CRM C Si Mn P S Cr Ni Mo N Co Sn B Ca V Pb Ø 37x20 mm, wrought

J 27AD 0.0477 0.411 1.59 0.022 0.0168 16.76 12.04 2.53 0.0629 0.089 0.0039 0.0018 0.0033 0.0041 0.00016 Edelstahl
Stainless Steel

J 27A Späne lieferbar; Chips available

RM C Si S P Mn Ni Cr Mo Cu Co W Ti Ta B Sb

4 12853J 0.050 0.99 0.016 0.016 1.17 11.92 17.2 2.74 0.114 0.06 0.12 0.027 0.03 0.003 0.02

4 12855K 0.109 1.00 0.016 0.014 1.04 12.1 17.2 2.78 0.40 0.16 0.21 0.043 0.11 0.021 0.19

Zr Bi Ø 40x15 mm, cast

0.009 (0.007) AISI316 Edelstahl
<0.01 <0.005 Stainless Steel

RM C Si S P Mn Ni Cr Mo Cu Co Nb W Al Ti

4 14207J 0.06 1.55 0.011 0.011 1.04 12.48 19.97 0.23 0.24 0.01 0.26 3.05 – –

4 14211P 0.112 1.75 0.018 0.016 0.65 12.8 25.7 0.31 0.28 0.056 0.15 2.80 – –

4 14212Q 0.069 2.50 0.041 0.058 0.66 10.33 20.90 0.540 5.56 0.241 0.612 3.32 (0.013) (0.018)

4 14215K 0.126 0.56 0.016 0.016 1.08 15.70 23.8 0.046 0.03 0.016 (0.016) 2.89 – 0.08

4 14216N 0.05 1.54 0.034 0.026 0.748 12.61 22.03 0.228 0.210 0.232 0.27 2.00 (0.004) (0.005)

4 14219J 0.10 1.48 0.048 0.047 0.48 12.39 21.71 0.19 0.23 – 0.19 4.07 – –

V N Cd Ø 40-43x15-20 mm

– – – Edelstahl

– – – Stainless Steel

0.152 0.121 0.0015

0.06 – –

0.040 0.142 – –

– – – –

cast

RM C Si S P Mn Ni Cr Mo Cu Co Al Ti Ta Sn B N V Ø 40x15 mm

4 12533Y 0.03 0.37 0.032 0.011 1.13 5.04 18.8 1.05 0.18 0.055 0.011 0.14 (0.17) (0.03) (0.01) (0.014) – Edelstahl

4 12534T 0.07 0.81 0.043 0.014 0.54 8.10 17.56 2.02 0.10 0.05 0.02 0.21 – – – – – SS-Steel

4 12535BC 0.219 1.04 0.0656 0.071 0.29 15.05 17.80 4.15 0.081 0.055 0.037 0.43 – 0.017 – 0.056 0.048

4 12536R 0.165 0.65 0.13 0.053 0.47 11.9 14.8 2.53 0.048 0.09 0.11 0.47 0.15 0.018 0.022 – –

4 12537S 0.090 1.18 0.048 0.092 1.174 11.10 19.32 3.12 0.659 0.114 (0.011) 0.053 (0.15) 0.049 0.007 0.043 – ch-cast

RM C Si S P Mn Ni Cr Mo Cu Nb N V As Co B Ø 40-43x15-20 mm, cast

4 PH1M 0.107 0.236 0.031 0.053 1.49 5.21 16.17 0.172 3.11 0.071 0.238 (0.006) 0.003 0.004 – 17-4PH Edelstahl

4 PH2K 0.07 0.51 0.020 0.025 0.89 3.79 16.7 0.94 4.11 0.17 (0.013) – – – – FV 520 Stainless Steel

4 PH3L 0.157 1.70 0.039 0.023 0.399 6.03 7.47 0.996 7.06 0.65 0.0291 0.066 – 0.398 0.0046

4 PH4M 0.0347 0.647 0.061 0.0152 0.728 4.39 13.73 0.323 5.42 0.338 0.112 0.582 – 0.655 (0.0037) chill cast

4 PH5J 0.122 1.03 0.015 0.065 0.98 4.51 17.85 0.51 4.42 0.58 0.046 – – – –

4 PH6E 0.116 2.10 0.015 0.040 0.652 6.35 12.13 1.45 2.08 0.539 0.027 0.167 0.028 0.138 –

4 PH7E 0.10 1.40 0.021 0.031 1.49 5.58 13.15 2.53 0.79 0.29 0.060 – – – –

B R E I T L Ä N D E R G M B H

2.3.6

Edelstahl, aust.

Edelstahl, hoch leg.

(Stainless Steel, aust.)

(Stainless Steel, high alloy)

RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	B	Ca	Co	O	N	Nb	Sn	Ti
6 81P	0.026	1.35	0.023	0.012	0.36	0.19	10.06	18.15	0.41	(0.003)	0.0026	(0.0004)	0.21	(0.0064)	0.069	-	0.007	0.003
6 81N	0.053	1.83	0.028	0.017	0.56	0.25	8.42	19.72	0.36	0.003	0.0007	(0.0006)	0.11	-	0.234	0.013	0.010	<0.005
6 81V-1	0.032	1.76	0.023	0.0012	0.55	0.10	9.13	19.14	0.134	0.003	-	-	0.056	-	0.048	0.011	0.003	0.002
6 10C	0.063	1.74	0.025	0.028	0.45	0.26	8.46	18.23	0.35	0.003	0.0004	0.0007	0.12	0.0054	0.0850	0.010	0.007	0.002
6 81T	0.050	1.71	0.029	0.021	0.48	0.31	8.50	18.36	0.38	0.002	0.0005	(0.0003)	0.136	-	-	(0.005)	-	-
6 9722	0.031	1.70	0.020	0.0014	0.55	0.108	9.15	19.13	0.128	-	-	-	0.054	-	0.047	-	-	-
6 84J	0.017	1.46	0.035	0.025	0.51	0.46	10.34	17.12	2.08	(0.002)	0.0005	0.0010	0.23	0.0063	0.059	0.024	0.007	(0.002)

V W As Ø 35-45x12 mm, wrought

0.078 0.037 - AISI 304L Edelstahl
 0.088 0.044 - AISI 304L Stainless Steel
 0.072 0.023 - AISI 304+N
 0.045 0.025 0.004 AISI 304
 0.044 0.03 - AISI 304
 0.076 - - AISI 304
 0.09 0.054 - AISI 316L

RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn	Al	V	Co	Ti	Nb	W	B
6 82D	0.058	1.85	0.020	0.009	0.63	0.16	14.12	22.40	0.144	0.042	(0.002)	0.087	0.042	0.005	0.053	0.028	0.0040
6 82E	0.062	1.61	0.027	0.001	0.58	0.26	12.49	22.38	0.31	0.12	0.006	0.064	0.12	0.003	0.062	0.041	0.0024
6 83F	0.055	1.78	0.023	0.003	0.47	0.074	20.5	24.5	0.20	(0.006)	-	(0.04)	0.19	(0.008)	0.11	(0.08)	-
6 9841	0.067	1.69	0.024	0.024	0.54	0.356	19.55	24.30	0.57	0.006	<0.006	0.070	0.116	(0.002)	0.070	0.06	0.0026
6 9842	0.059	1.50	0.025	0.0016	0.99	0.147	20.02	24.19	0.111	0.005	0.014	0.075	0.237	0.003	0.026	0.011	0.0025
6 9941	0.021	1.78	0.027	0.024	0.33	0.424	13.68	18.48	3.24	0.007	0.004	0.062	0.178	(0.002)	0.015	0.068	0.0025
6 9942	0.021	1.84	0.025	0.006	0.49	0.305	13.55	18.21	3.30	0.006	0.004	0.072	0.086	(0.002)	0.005	0.032	0.0014
6 317L	0.027	1.17	0.029	0.0014	0.67	0.23	13.53	18.16	3.07	0.005	(0.005)	0.09	0.14	-	0.031	0.018	0.0013
6 85D	0.049	1.69	0.025	0.024	0.55	0.45	10.03	17.09	0.59	(0.006)	0.13	0.134	0.97	0.48	0.065	0.06	0.0006
6 321A	0.061	1.22	0.030	0.012	0.48	0.284	9.38	17.20	0.20	0.010	0.038	0.066	0.15	0.51	0.021	0.06	(0.0005)
6 321C	0.037	1.72	0.025	0.022	0.58	0.28	10.58	17.16	0.30	0.006	0.044	0.079	0.048	0.38	0.008	(0.03)	(0.0005)
6 86F	0.054	1.30	0.021	0.0011	1.22	0.23	34.99	18.74	0.24	0.004	(0.007)	0.134	0.098	(0.006)	0.19	(0.03)	0.0026
6 87F	0.055	1.66	0.025	0.026	0.64	0.28	10.21	17.37	0.29	0.004	0.004	0.13	0.18	0.005	0.59	0.050	0.0007
6 347A	0.051	1.50	0.026	0.020	0.54	0.31	9.20	17.44	0.326	0.007	(0.002)	0.10	0.054	(0.002)	0.79	(0.03)	(0.0004)
6 347B	0.051	1.57	0.028	0.026	0.51	0.15	9.16	17.24	0.38	0.006	0.002	0.04	0.05	(0.002)	0.71	(0.005)	0.0036

O N Ca As Pb Sb Ta Ø 35-45x12 mm, wrought

0.007 0.070 0.0007 - - - AISI 309 Edelstahl
 - 0.072 0.0014 - - - AISI 309 Stainless Steel
 - - - - - - AISI 310
 (0.011) 0.064 (0.0002) (0.003) (0.001) (0.006) - AISI 310 CRM
 (0.0044) 0.037 0.0010 (0.002) - - AISI 310 CRM
 (0.0058) 0.036 (0.0003) (0.010) - - AISI 317L CRM
 (0.0023) 0.071 0.0014 (0.004) - - AISI 317L CRM
 0.007 0.056 (0.001) - (0.003) - 0.007 AISI 317L
 0.0014 0.016 0.0004 0.006 0.0004 0.001 - AISI 321
 0.0013 0.0075 (0.0002) (0.006) - - (0.002) AISI 321
 (0.0011) 0.0082 (0.0001) (0.004) - - - AISI 321
 - 0.035 (0.001) (0.003) (0.001) - - AISI RA330
 0.0048 0.038 - - - - AISI 347
 0.0047 0.044 (0.0002) (0.003) - - (<0.004) AISI 347
 0.005 0.056 (0.0002) (0.003) - - (<0.004) AISI 347

B R E I T L Ä N D E R G M B H
2.3.8

Edelstahl, aust.
Edelstahl, hoch leg.

(Stainless Steel, aust.)
(Stainless Steel, high alloy)

RM C Mn P S Si Cu Ni Cr Mo Ti Ø 40x25 mm

8 PV111/1 0.0226 1.538 0.019 0.026 0.485 0.105 8.57 18.49 0.173 – AISI 304L
8 PV112/1 0.047 1.577 0.018 0.023 0.515 0.102 11.14 17.56 2.03 0.394 AISI 316Ti

RM C Mn P S Si Cu Ni Cr Mo W Co V Nb Al Ti Ca B

6 9812 0.031 0.485 0.018 0.004 0.43 1.65 6.61 14.82 0.76 0.025 0.110 0.088 0.645 (0.002) (0.005) 0.0012 (0.0003)
6 9811 0.027 0.380 0.016 0.0010 0.36 1.63 6.55 14.87 0.744 0.013 0.055 0.086 0.62 (0.003) (0.003) 0.0014 (0.0003)
6 95A 0.035 0.58 0.026 0.004 0.46 1.50 6.42 14.72 0.73 0.02 0.081 0.052 0.55 0.002 (0.003) 0.0008 0.0010
6 96A 0.009 0.04 0.007 0.004 0.06 2.07 8.38 11.62 0.021 – 0.038 0.07 0.26 0.08 1.18 – (0.0017)
6 SS1961 0.009 0.049 0.008 0.0038 0.056 2.11 8.31 11.61 0.020 (0.01) 0.036 0.074 0.26 0.069 1.16 – 0.0022
6 SS1962 0.008 0.06 0.006 0.0025 0.06 2.22 8.32 11.42 0.008 (<0.02) (0.015) 0.071 0.27 0.067 1.11 – 0.0018

N O As Ø 31-50x12 mm, wrought

0.0195 (0.007) (0.005) Custom 450 CRM
0.0196 (0.0060) (0.003) Custom 450 CRM
0.0255 0.0043 – Custom 450
– – – Custom 455
0.0025 (0.002) 0.004 Custom 455
0.0025 (0.001) 0.002 Custom 455

RM C Mn P S Si Cu Ni Cr Mo W Co V Nb Al Sn N Ca

6 253 0.094 0.58 0.018 <0.001 1.81 0.14 10.89 20.68 0.21 0.03 0.15 0.050 0.017 0.016 0.006 0.146 –
6 318 0.020 1.39 0.019 0.002 0.48 0.17 5.61 22.30 3.31 <0.02 0.101 0.064 – 0.006 0.004 0.159 –
6 183A 0.172 0.35 0.016 0.0040 0.37 0.093 1.85 12.14 0.12 2.60 0.036 0.090 0.006 0.002 0.003 0.0256 0.0020
6 184A 0.035 0.06 0.007 0.001 0.080 0.041 8.34 12.66 2.20 0.032 0.036 0.014 (0.006) 1.00 (0.002) 0.0045 (0.0003)
6 185A 0.033 0.49 0.022 0.002 0.38 3.41 4.43 14.46 0.30 (0.014) 0.026 0.048 0.32 0.002 0.007 0.027 –
6 9621 0.035 0.31 0.017 0.0011 0.468 3.42 4.61 14.93 0.063 (0.01) 0.029 0.096 0.27 0.003 0.003 0.013 (0.0001)
6 9622 0.032 0.63 0.019 0.004 0.42 3.34 4.34 14.34 0.27 (0.020) 0.040 0.074 0.33 0.002 0.006 0.028 –
6 192A 0.066 0.768 0.021 <0.002 0.300 0.334 7.01 16.44 0.28 0.048 0.114 0.077 0.208 0.98 0.008 0.029 (0.0006)
6 186A 0.040 0.72 0.008 0.005 0.19 0.016 35.86 0.16 0.003 <0.03 0.028 0.001 <0.002 (0.001) (0.002) 0.0026 –
6 187A 0.022 0.52 0.017 0.0025 0.26 3.10 33.06 19.75 2.06 – 0.32 0.10 0.57 (0.009) 0.003 0.0157 –
6 187C 0.020 0.77 0.024 <0.002 0.77 3.17 32.93 20.16 2.07 – 0.096 0.059 0.36 0.10 0.004 0.022 –
6 188A 0.050 0.139 0.015 0.0049 0.15 0.099 24.61 14.02 1.10 0.055 0.18 0.24 0.050 0.19 0.002 0.0029 –

Ti Se B Ce Ø 35-41x12 mm, wrought

0.005 – – 0.044 235MA
(0.003) – (0.0004) – 2205
0.002 – (<0.0005) – Greek Asc.
0.051 – – – PH13-8Mo
(0.001) – – – 15-5 PH
(0.001) – 0.0004 – VAR 15Cr-5Ni
(0.001) – 0.0004 – 15Cr-5Ni
0.083 – (0.0003) – 17-7 PH
<0.003 0.229 – – Invar 36
(0.002) – 0.0022 (0.025) Carp. 20Cb3
(0.001) – (0.0019) – Alloy 20
2.21 – 0.0065 – A 286

B R E I T LÄNDER GMBH

Edelstahl, aust.
Edelstahl, hoch leg.(Stainless Steel, aust.)
(Stainless Steel, high leg.)

2.3.9

RM C Mn Si P S Cr Ni Mo V W Co Cu Nb Ti Sn Ø 40x25 mm, wrought

7316 0.065 1.89 0.43 0.046 0.025 17.5 8.45 0.50 0.04 (0.08) 0.22 0.35 (0.06) 0.004 0.014 Edelstahl: SS, aust.

RM C Mn Si P S Cr Ni Mo Cu Co V W Nb Sn Ag

CT 303 0.070 1.64 0.58 0.029 0.31 17.78 9.08 0.41 0.49 0.16 0.044 - - 0.007 0.0003

CT 304 0.063 0.78 0.56 0.026 0.023 18.57 9.60 0.33 0.34 0.20 0.037 - 0.043 0.017 0.0007

CT 305 0.067 1.85 0.55 0.025 0.022 18.58 11.95 0.45 0.29 0.22 0.078 - - -

CT 309 0.051 1.91 0.50 0.019 0.002 23.71 12.15 0.08 0.10 0.13 0.05 - - -

CT 316 0.061 1.67 0.69 0.029 0.023 17.60 12.61 2.45 0.25 0.14 0.051 - - 0.006 0.0005

Pb Se Al Ti Ø 32x16 mm, wrought

0.001 - - - AISI 303

<0.001 - - - AISI 304

- - - AISI 305

- - 0.002 - AISI 309 38x36x24 mm

0.001 - - - AISI 316

RM C Mn Si P S Cr Ni Mo Cu Co V W Nb Sn Ag

CT 061 0.043 0.69 0.40 0.010 0.012 18.25 8.40 0.49 0.10 0.06 0.03 0.02 0.01 0.006 0.002

CT 689 0.062 1.50 0.80 0.005 0.006 17.48 12.52 2.48 0.10 0.12 0.030 0.005 0.008 0.005 0.0028

Pb Al Ti B Ø 32x16 mm, wrought

0.0005 0.002 0.03 - AISI 304M

0.0012 0.030 0.005 0.0011 AISI 316M

RM C Mn Si P S Cr Ni Mo Cu Co V N Nb Sn Ag Pb

CT 450 0.036 0.39 0.29 0.014 0.006 15.20 6.36 0.80 1.49 0.16 0.043 0.028 0.67 0.008 0.0013 0.001

CT 455 0.012 0.074 0.13 0.010 0.005 11.37 8.22 0.027 2.32 - 0.002 0.28 0.004 0.0002 <0.001

CT 123A 0.003 0.035 0.031 0.007 <0.0005 11.67 11.10 0.92 0.010 0.016 0.014 0.003 <0.001 - - -

CT 630 0.036 0.39 0.63 0.018 0.013 15.94 4.20 0.11 3.25 0.11 0.022 0.028 0.36 0.007 0.0004 0.001

CT 20CB-3 0.034 0.19 0.38 0.017 0.003 19.63 33.55 2.25 3.28 0.035 0.053 - 0.86 0.003 0.0019 0.002

B Ti Se Ø 32x16 mm, wrought

- - - Custom 450

0.0024 1.18 - Custom 455

0.0021 1.58 - Custom 465 CRM

0.0018 - - Custom 630

0.0023 - - 20CB-3

RM	Al	B	C	Co	Cr	Cu	Mn	Mo	N	Nb	Ni	O	P	S	Se	Si	Sn
IA 1C	0.002	(0.0004)	0.068	0.309	17.35	0.51	1.87	0.583	0.0344	0.056	8.64	0.0049	0.032	0.378	-	0.634	0.010
IA 253A	0.003	0.0003	0.041	0.088	17.90	0.223	1.50	0.348	0.0373	0.016	9.17	0.009	0.140	0.0089	0.21	0.50	0.01
IA 2F	0.003	0.0004	0.041	0.070	18.37	0.40	1.48	0.20	0.057	0.003	8.09	0.0087	0.043	0.028	-	0.27	0.008
IA 162B	0.003	0.003	0.022	0.30	18.35	0.81	1.76	0.482	0.0241	0.032	10.25	0.004	0.029	0.025	-	0.635	0.009
IA 3C	0.004	0.0003	0.066	0.078	22.28	0.130	1.573	0.195	0.037	0.013	14.88	0.015	0.023	0.027	-	0.27	0.003
IA 4C	0.01	0.0003	0.064	0.098	23.59	0.230	1.69	0.224	0.039	0.013	19.3	0.0054	0.029	0.0017	-	0.454	0.007
IA 5D	0.005	(0.0005)	0.021	0.143	16.56	0.168	1.78	2.11	0.056	(0.004)	10.38	0.0097	0.040	0.020	-	0.458	0.004
IA 163C	0.004	0.0005	0.013	0.178	17.16	0.43	1.60	2.03	0.071	0.013	10.36	0.0046	0.029	0.026	-	0.37	0.013
IA 153B	0.006	0.0022	0.015	0.115	18.13	0.408	1.58	3.12	0.0158	0.008	13.19	0.0052	0.031	0.0082	-	0.28	0.014
IA 6C	0.064	0.0003	0.038	0.139	17.61	0.130	1.73	0.090	0.027	0.003	9.23	0.0021	0.038	0.0087	-	0.61	0.005
IA 7B	0.023	-	0.062	0.069	19.32	0.21	1.47	0.19	0.0130	0.023	35.84	0.0026	0.018	(0.001)	-	1.38	0.004
IA 8C	0.003	0.0008	0.060	0.146	17.53	0.46	1.50	0.70	0.054	0.67	9.15	0.0054	0.030	0.027	-	0.43	0.011
IA 154A	0.008	-	0.39	0.021	12.82	0.044	0.47	0.052	0.0294	0.004	0.19	(0.0068)	0.018	0.003	-	0.35	0.004
IA 205B	0.009	0.0003	0.220	0.025	11.72	0.149	0.68	0.97	0.049	0.018	0.702	0.0016	0.014	0.001 As=0.005	0.37	0.006	
IA 15B	0.006	-	0.047	0.24	14.53	1.53	0.39	0.82	0.0355	0.65	6.94	0.0039	0.013	0.001	-	0.33	0.009
IA 16B	0.062	(0.0018)	0.0067	0.027	11.44	2.23	0.026	0.016	0.0022	0.25	6.28	0.0011	0.007	0.0025	-	0.039	0.004
IA 19B	0.010	0.001	0.021	0.098	19.98	0.174	9.31	0.275	0.250	0.057	6.83	0.0061	0.021	0.0020	-	0.48	0.005
IA 17B	(0.003)	-	0.032	0.080	21.34	0.17	5.12	2.30	0.33	0.22	13.36	0.0042	0.033	0.003	-	0.38	0.005
IA 18B	0.006	(0.002)	0.085	0.124	16.37	0.362	8.58	0.31	0.157	0.004	8.50	0.0016	0.032	0.0012	-	3.67	0.003

Ti V W Ø 31x18.5 mm + 31x5 mm

0.002	0.107	0.057	AISI 303	Edelstahl	IA SHTS30 - 30 AISI Typproben als Satz erhältlich 30 AISI pre-selected samples available as set
0.002	0.106	0.10	AISI 303Se	Stainless Steel	
0.001	0.036	0.021	AISI 304		
0.002	0.117	0.10	AISI 304L		
0.004	0.166	0.032	AISI 309		
0.003	0.078	0.024	AISI 310		
0.008	0.029	0.016	AISI 316		
<0.005	0.085	0.046	AISI 316L		
0.002	0.031	0.020	AISI 317L		
0.22	0.039	0.013	AISI 321		
(0.005)	0.048	(0.031)	AISI 330	IA 1C(C) - 18B(C)	Späne lieferbar 100 g Chips available
0.002	0.047	0.140	AISI 347		
0.002	0.045	0.011	AISI 420		
0.003	0.262	1.1	AISI 422		
0.005	0.033	0.12	Custom 450		
1.11	0.067	0.011	Custom 455		
0.006	0.102	0.022	Nitronic 40		
(0.002)	0.20	0.093	Nitronic 50		
0.006	0.058	0.020	Nitronic 60		

B R E I T L Ä N D E R G M B H
2.4.4

Schnellarbeitsstahl
Werkzeugstahl
(High Speed Steel)
(Toolsteel)

RM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Co	W	V	Ø 40x15 mm, cast
4 14944D	0.62	0.17	0.01	0.02	0.23	0.20	2.87	0.14	0.10	0.15	15.5	1.00	Schnellarbeitsstahl High Speed Steel
4 14945D	0.67	0.26	0.04	0.03	0.72	0.30	3.97	0.23	0.12	0.22	16.8	0.55	
4 14946D	0.85	0.46	0.05	0.05	0.53	1.06	5.06	0.21	0.25	0.44	16.9	1.03	
4 14948D	0.83	0.26	0.01	0.01	0.65	0.30	4.04	0.14	0.04	0.16	18.8	0.65	
4 14952D	0.90	0.32	0.05	0.05	0.64	0.30	4.93	0.32	0.02	0.02	18.0	1.24	

RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	As	N	O	Ti
6 9-4-30	0.316	0.22	0.008	<0.002	0.06	0.088	7.25	1.00	1.01	0.004	-	0.09	4.46	-	0.0014	-	-
6 32D	0.85	0.30	0.027	0.0022	0.25	0.039	0.053	4.14	4.92	0.018	6.15	1.82	0.010	-	0.018	-	-
6 33D	0.515	0.306	0.016	0.020	0.312	0.040	0.059	1.28	0.050	0.008	2.65	0.221	0.045	-	-	-	-
6 33E	0.49	0.29	0.022	0.005	0.20	0.038	0.08	1.25	0.045	-	2.75	0.19	0.006	-	-	-	-
6 H-19	0.404	0.318	0.014	0.011	0.29	0.055	0.114	4.27	0.356	(0.356)	4.02	2.05	4.17	0.0056	0.0190	0.0071	(0.002)
6 35D	0.879	1.13	0.021	0.024	0.22	0.14	0.13	0.495	0.035	(0.005)	0.46	0.18	0.012	-	-	-	-
6 36D	0.97	0.68	0.021	0.007	0.27	0.060	0.089	5.25	0.96	0.010	0.028	0.29	0.010	0.002	0.0108	-	-
6 38C	0.60	0.81	0.011	0.012	2.08	0.26	0.24	0.28	0.41	0.015	0.004	0.21	0.036	-	0.0081	-	-
6 39B	0.67	0.62	0.009	0.019	0.21	0.16	1.45	0.79	0.17	0.011	-	(0.01)	(0.02)	-	-	-	-
6 40B	0.71	2.28	0.020	0.006	0.35	0.076	0.089	1.18	1.07	0.002	0.11	0.10	0.020	0.004	0.0076	(0.0015)	0.002
6 41A	1.50	0.93	0.004	0.001	0.97	0.034	0.17	0.20	0.19	0.010	(<0.003)	(0.003)	0.006	0.002	0.007	0.002	0.004
6 TS7	0.529	0.70	0.016	0.010	0.27	0.05	0.10	3.18	1.34	-	0.19	0.35	0.043	-	-	-	-
6 M-47	1.14	0.20	0.020	0.002	0.464	0.080	0.17	3.72	9.24	(0.002)	1.36	1.23	4.99	0.006	0.0219	0.0037	(0.004)
6 A10	1.41	1.75	0.016	0.022	1.15	0.16	1.82	0.24	1.53	0.006	<0.005	(0.004)	(0.010)	-	-	-	-
6 10V	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	1.30	<0.002	0.013	9.50	0.009	-	0.064	-	0.004
6 49	0.36	0.33	0.014	0.014	0.93	0.070	0.20	3.51	2.40	0.004	0.31	0.62	2.00	-	0.019	-	-

Sn	Pb	Nb	Ø 38-41x12 mm, wrought	Werkzeugstahl
-	-	-	AISI 9-4-30	AISI M 2
-	-	-	AISI S-1	Tool Steel
-	-	-	AISI S-1	
0.0056	-	0.008	AISI H-19	
-	-	-	AISI O-1	
0.016	-	-	AISI A-2	
0.022	0.022	-	AISI S-5	
-	-	-	AISI L-6	
0.005	-	-	AISI A-6	
0.002	-	(<0.002)	AISI O-6	
-	-	-	AISI S-7	
0.006	-	(0.004)	AISI M-47	
-	-	-	AISI A-10	
0.003	-	-	HIP-Technol.	
-	-	-	HIP-Technol.	

RM	C	Mn	Si	P	S	Cr	Ni	Mo	V	W	Co	Cu	Ø 40x25 mm, wrought
7 208	0.31	0.33	1.00	0.013	(0.006)	1.05	0.11	0.21	(<0.01)	4.20	(<0.05)	0.07	Werkzeugstahl/Schnellarbeitsstahl
7 214	0.87	0.34	0.31	0.023	(0.008)	4.24	0.17	0.34	0.99	18.50	0.25	0.09	Tool Steel/High Speed Steel
7 220	0.31	0.32	0.31	0.018	(0.015)	2.75	0.15	0.02	0.29	10.54	(<0.05)	0.15	

RM	C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Co	V	W	Ø 32x16 mm, wrought
CT M1	0.80	0.30	0.22	0.012	0.005	3.91	0.12	8.22	0.087	-	1.05	1.58	Werkzeugstahl/Schnellarbeitsstahl
CT M2	0.82	0.33	0.27	0.012	0.004	4.03	0.25	4.96	0.06	0.05	1.81	6.47	Toolsteel/High Speed Steel
CT M7	1.00	0.29	0.34	0.012	0.003	3.60	0.10	8.49	0.066	-	2.02	1.78	
CT M10	0.88	0.27	0.30	0.015	0.004	3.97	0.14	7.89	0.061	0.012	1.99	<0.05	Probenbezeichnung kennzeichnet AISI-Type
CT D2	1.53	0.48	0.40	0.013	0.005	11.46	0.10	0.75	0.04	0.02	0.89	<0.01	Sample number indicates AISI-Type
CT H13	0.39	0.30	1.05	0.015	0.005	5.23	0.10	1.36	0.061	-	1.02	-	
CT A2	0.95	0.72	0.40	0.010	0.004	5.13	0.10	1.05	0.06	-	0.22	-	
CT O1	0.91	1.27	0.36	0.009	0.004	0.49	0.06	0.07	0.05	-	0.25	0.51	
CT X35568	1.36	0.14	0.19	0.006	0.002	0.076	0.054	0.017	0.10	-	-	3.20	F2
CT X27081	1.32	0.20	0.24	0.004	0.001	0.052	0.031	0.008	0.026	-	-	3.39	F2

RM	A1	B	C	Co	Cr	Cu	Mn	Mo	N	Nb	Ni	O	P	S	Si	Sn
IA 39B	0.006	-	0.99	0.014	4.79	0.10	0.54	1.01	0.0096	0.006	0.14	-	0.017	0.003	0.35	0.004
IA 40B	(0.006)	(0.0010)	0.68	0.015	1.04	0.050	1.98	1.22	0.0107	0.005	0.096	(0.0014)	0.012	0.003	0.39	0.004
IA 41B	0.014	-	1.49	0.025	(12.51)	0.035	0.36	0.80	0.0128	-	0.095	(0.0024)	0.021	0.005	0.30	0.004
IA 42B	0.013	(0.0005)	0.38	0.013	5.10	0.089	0.36	1.23	0.0105	0.004	0.18	0.0026	0.014	0.005	0.99	0.005
IA 43B	0.021	0.0002	0.711	0.012	0.651	0.180	0.56	0.206	0.0093	0.004	1.39	0.0016	0.008	0.013	0.251	0.013
IA 44B	-	-	0.84	0.41	3.86	0.0072	0.27	4.79	0.0252	0.016	0.18	0.0028	0.014	0.006	0.39	(0.008)
IA 45B	0.010	(0.0001)	1.42	0.004	0.061	0.018	0.90	0.24	0.0080	0.002	0.024	0.0005	0.010	0.008	0.92	0.008
IA 46B	0.011	0.0003	0.45	0.013	1.09	0.147	0.27	0.222	0.0069	0.003	0.108	0.002	0.019	0.0040	0.89	0.016
IA 47B	0.014	(<0.001)	0.59	0.007	0.23	0.17	0.79	0.20	0.0092	(0.002)	0.090	(0.0014)	0.017	0.006	1.96	0.008
IA 48B	(0.006)	-	0.74	(0.040)	4.14	0.070	0.28	0.093	0.0096	0.004	0.080	(0.0125)	0.020	0.023	0.28	(0.009)

Ti	V	W	As	Ø 31x18.5 mm + 31x5 mm
0.003	0.22	(0.026)	-	AISI A2 Werkzeugstahl als Satz erhältlich: IA TS10
0.003	0.014	0.013	-	AISI A6 Tool Steel available as set
0.005	0.76	(0.022)	-	AISI D2
0.003	0.94	0.012	-	AISI H13
0.0047	0.0035	<0.005	0.005	AISI L6
0.004	1.83	5.98	-	AISI M2
0.002	0.003	(0.004)	0.002	AISI O6 IA 39B(C) - 48B(C) Späne erhältlich 100 g
0.007	0.170	1.96	(0.01)	AISI S1 Chips available
0.010	0.17	(0.016)	-	AISI S5
(0.004)	1.12	(17.26)	-	AISI T1

CRM	C	Si	Mn	P	S	Cr	Ni	Al	As	Co	Cu	N	Sn	Ti	V	Ca	Zn	Ø 30x25mm
8 TL-1668	0.2146	1.645	1.643	0.0137	0.0012	0.0173	0.0164	0.0371	0.0016	0.0031	0.0108	0.0043	0.0047	0.0032	0.0016	0.0019	0.0008 TRIP 800	
CRM	C	Mn	P	S	Si	Cr	Mo	Ni	Al	Co	Cu	N	V	Ø 50x10 mm, cast				
5 491/2	0.994	16.73	0.0494	0.0112	1.101	1.482	0.608	0.0745	0.110	-	(0.04)	0.0215	0.0839	Stahl, hoch Mn				
5 494/2	1.398	13.37	0.0421	0.0032	0.373	0.668	0.101	0.732	0.0022	(0.43)	0.166	0.0146	(0.025)	Steel, high Mn				
5 495/4	0.797	13.11	0.091	0.0128	0.674	2.223	0.266	1.620	0.0082	0.0120	0.0222	0.0416	0.0525					
CRM	C	Si	Mn	P	S	Cr	Mo	Ni	As	Co	Cu	N	V	Ø 40x20 mm				
EC 294-1D	0.0657	0.283	18.68	0.0271	0.00031	17.98	0.0861	0.429	0.0037	0.0288	0.0242	0.566	0.0694	Mn-Stahl; Mn-Steel 1.3816				
CRM	C	Mn	P	S	Si	Cr	Ni	V	Ti	Mo	Nb	Ø 32x42 mm, wrought						
CI 16703-1	0.22	6.01	0.037	0.0033	0.34	14.08	9.60	0.32	0.052	0.94	0.25	Stahl, hoch Mn						
CI 16703-2	0.22	7.21	0.018	0.0031	0.27	16.05	4.96	0.53	0.070	0.79	0.35	Steel, high Mn						
CI 16703-3	0.15	5.17	0.014	0.0055	0.21	10.43	11.01	0.81	0.102	1.20	0.12							
CI 16703-4	0.34	8.44	0.021	0.0042	0.53	12.43	8.14	1.07	0.117	0.72	0.18	nur Satz/set only						
CI 16703-5	0.37	9.80	0.033	0.0043	0.60	9.62	6.83	1.28	0.089	1.46	0.74							
CI 16703-6	0.48	11.07	0.035	0.0130	1.03	8.43	5.90	1.72	0.270	1.79	0.43							
CRM	C	Mn	P	S	Si	Cr	Ni	Mo	Cu	Co	W	V	Ti	Al	Nb	Sn	N Ø 35x35x20mm	
CT 035A	0.102	12.04	0.023	0.002	0.59	18.48	1.81	0.28	0.17	0.037	0.002	0.058	0.001	<0.004	0.004	0.003	0.33 Stahl, hoch Mn	
CT 129A	0.030	9.31	0.022	<0.001	0.40	19.62	6.86	0.25	0.152	0.102	0.03	0.144	-	0.014	0.025	-	0.264 Steel, high Mn	
RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Co	Ti	Al	B	N	Nb	O	Sn	
6 177	0.344	3.26	0.029	0.010	0.79	0.32	7.40	23.28	0.30	0.10	0.002	0.001	(0.0007)	0.32	0.042	(0.006)	(0.006)	
6 180A	0.018	5.05	0.012	0.001	0.32	0.067	13.19	21.09	2.04	0.039	(0.002)	0.012	(0.0023)	0.334	0.20	0.003	(0.002)	
6 191	0.098	5.71	0.024	0.023	3.66	0.33	5.34	16.33	0.36	0.11	0.012	(0.002)	(0.0006)	0.117	0.024	0.002	(0.006)	
6 203MN	0.048	5.99	0.026	0.30	0.46	1.88	5.50	16.75	0.18	0.06	(0.002)	(0.001)	(0.0010)	0.032	(0.004)	-	0.007	
6 181A	0.071	8.16	0.019	0.001	4.03	0.18	8.15	16.52	0.21	0.072	0.007	0.022	0.0009	0.148	0.017	0.0010	0.005	
6 190	0.022	9.72	0.015	0.001	0.46	0.072	6.74	19.57	0.15	0.044	0.002	(0.004)	0.0005	0.255	(0.004)	0.0045	0.003	
6 193	0.104	12.11	0.018	0.002	0.66	0.088	1.82	18.48	0.21	0.028	0.003	(0.003)	0.0007	0.37	0.014	(0.004)	0.004	
	V	W	Ta	Ca	Ø 32-41x12 mm, wrought													
	0.10	0.05	-	-	-	Stahl, hoch Mn												
	0.20	0.02	-	-	-	Nitronic 50	Steel, high Mn											
	0.083	0.033	0.002	-	-	-												
	0.054	0.03	-	-	-	203												
	0.094	0.04	-	-	-	Nitronic 60												
	0.11	0.015	-	-	-	21Cr6Ni9Mn												
	0.107	(0.007)	-	0.0020	0.0020	12Mn18Cr												
RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	Nb	Sn	V	Ø 32x17 mm, cast		
6 17A	0.588	19.38	0.043	0.005	0.22	0.135	0.060	1.37	0.52	0.052	0.013	0.038	0.06	0.012	0.016	Stahl, hoch Mn		
6 18A	1.13	11.30	0.019	0.043	0.64	0.029	0.36	0.22	0.049	0.019	0.009	0.042	0.05	0.007	0.32	Steel, high Mn		
6 19A	1.57	8.76	0.092	0.009	1.46	0.51	1.48	3.75	1.97	0.057	0.014	0.039	0.040	0.037	0.10			

RM	C	Mn	Si	S	P	Ni	Cr	Mo	Cu	Al	V	Sn	N	Nb	Ø 40x17 mm, chill cast		
4 MN1AG	0.529	19.50	0.315	0.0111	0.0115	1.42	1.74	0.751	0.0603	0.008	0.0150	0.085	0.027	0.319	Stahl, hoch Mn		
4 MN2Q	0.788	9.57	1.27	0.0198	0.0228	0.501	0.381	1.56	(0.16)	(0.008)	0.104	0.0683	0.0148	0.346	Steel, high Mn		
4 MN3R	1.33	11.14	1.01	0.0263	0.053	2.11	1.17	0.459	0.357	(0.026)	0.048	0.0319	0.030	0.416			
4 MN4X	1.327	13.76	0.812	0.0289	0.035	1.033	1.92	0.823	0.310	(0.015)	0.034	0.032	0.0217	0.063			
4 MN5R	1.463	7.62	1.48	0.030	0.025	1.60	3.75	1.98	0.56	(0.03)	0.0255	0.0111	0.0274	0.100			
RM	C	Mn	Si	S	P	Ni	Cr	Mo	Cu	Al	V	Sn	Ø 40x15 mm, cast				
4 15195P	1.64	12.06	1.45	0.018	0.062	0.09	0.11	0.30	0.12	0.08	0.33	0.05	Stahl, hoch Mn				
4 15196S	1.08	10.16	1.64	0.012	0.037	0.25	0.26	0.22	0.22	0.13	0.21	0.10	Steel, high Mn				
CRM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	32x16 mm, chill cast						
3 C1221	0.20	0.102	0.090	0.112	0.876	0.041	0.067	0.049	0.038	0.111	AISI 1211 Mod						
RM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Al	Pb	V	As	Co	N	Ø 41x13 mm, wrought
6 70B	0.40	0.27	0.022	0.009	0.90	0.25	1.00	0.205	0.13	-	(0.024)	0.135	-	-	-	-	AISI 41140
6 73B	0.200	0.250	0.030	0.009	0.83	0.416	0.512	0.170	0.141	0.008	0.022	0.139	(<0.002)	0.004	0.008	0.0113	AISI 86L20
6 74C	0.077	(0.002)	0.294	0.082	0.94	0.011	0.019	0.008	0.005	(<0.002)	(<0.002)	0.328	0.0016	0.004	-	0.0040	AISI 12L14
RM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Co	V	N	Al	Ø 40x15 mm, cast		
4 MSFM1J	0.0098	0.351	0.364	0.0778	1.109	0.0205	0.017	0.249	0.0056	0.0041	0.0019	0.0026	0.0060	0.0024	Automatenstahl, hoch S und P		
4 MSFM2H	0.269	0.505	0.193	0.060	1.83	0.040	0.060	0.291	0.0085	(0.003)	0.0033	(0.0008)	(0.003)	(0.002)	Resulphurized/Rephosphorized Steel		
4 MSFM3F	0.55	0.52	0.087	0.060	2.10	-	-	0.27	-	-	-	-	-	-			
4 MSFM4A	0.225	0.45	0.22	0.037	0.96	6.05	1.65	0.96	0.43	0.015	0.025	0.015	0.025	0.005	chill cast		
RM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Ti	Co	Al	V	N	Ø 41-44x19 mm, wrought	
6 42	0.516	0.24	0.073	0.021	1.24	0.18	0.67	0.19	0.25	0.012	(0.003)	0.012	0.020	0.003	0.0080	AISI 4150 + S Automatenstahl	
6 42A	0.52	0.258	0.078	0.012	1.08	0.147	0.80	0.195	0.285	(0.009)	-	(0.007)	0.025	0.004	0.008	AISI 4150 + S Fr. Cutting St.	
6 52D	0.436	0.18	0.088	0.068	0.97	0.18	0.16	0.09	0.060	0.004	(0.004)	0.012	0.028	0.002	0.0025	AISI 1140 + P	
6 65C *	0.150	0.24	0.115	0.007	1.19	0.063	0.066	0.012	0.24	0.02	-	(0.007)	(0.002)	0.002	0.0084	AISI 1117	
6 66B *	0.418	0.03	0.110	0.018	1.57	0.033	0.094	0.019	0.031	0.001	<0.002	0.005	0.002	0.002	(0.006)	AISI 1141 * = nur für RFA	
6 66K *	0.051	(0.004)	0.322	0.062	0.86	0.012	0.006	0.003	0.013	<0.001	<0.002	0.005	0.002	0.001	(0.0074)	AISI 1215 only for XRF	
6 3993	0.152	0.260	0.094	0.012	1.16	0.045	0.072	0.010	-	0.006	As=0.004	0.006	0.002	0.002	0.0071	AISI 1117 CRM	
RM	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Sn	Pb	As	Sb	Al	N	Ø 40x40 mm, wrought	
G 120	0.60	0.34	0.026	(0.049)	0.40	0.085	0.20	0.10	0.008	0.077	0.065	0.031	0.033	0.0115	Automatemstahl		
G 121	0.39	(0.056)	0.097	0.057	1.18	0.029	0.036	0.032	0.059	0.011	0.002	0.017	0.016	0.0125	Free Cutting Steel		
G 122	0.27	0.43	0.21	0.073	1.33	0.25	0.19	0.25	0.12	(0.020)	0.007	0.019	(0.027)	0.0110			
G 123	0.25	0.23	0.38	0.030	1.57	0.057	0.16	0.093	(0.007)	0.030	0.033	0.030	0.032	0.0171			
G 124	0.10	(0.019)	0.28	0.082	0.60	0.046	0.11	0.060	0.009	(0.002)	0.004	0.002	0.005	0.0059			
G 125	0.029	0.15	(0.057)	(0.018)	0.95	0.023	0.18	0.044	0.002	-	0.065	0.014	(0.007)	-			

CRM	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	Al	V	As	Ti	Co	Nb	Ø 31x19 mm	
3 1138a	0.118	0.25	0.35	0.035	0.056	0.09	0.10	0.13	0.05	(0.067)	0.020	(<0.005)	(0.0012)	-	-	Gußstahl	
3 1139a	0.790	0.80	0.92	0.012	0.013	0.47	0.98	2.18	0.51	(0.13)	0.26	(<0.005)	(0.004)	-	-	Cast Steel	
3 1173	0.423	1.28	0.19	0.033	0.092	0.204	4.06	2.70	1.50	-	0.42	-	(0.015)	0.076	(0.045)		
CRM	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	Al	V	As	Ti	Co	Ø 31x19 mm, chill cast		
3 C1173	0.453	1.38	0.174	0.031	0.092	0.204	4.04	2.63	1.46	(0.005)	0.42	(0.002)	0.037	0.064	Gußstahl; Cast Steel		
CRM	C	Si	Mn	P	S	Cr	Mo	Ni	Co	Cu	V	W	Ø 35x30 mm, wrought				
EC 290-1D	0.91	0.08	0.24	0.016	0.016	4.18	0.481	0.33	5.12	0.08	1.92	6.24	Sonderleg.; Special Alloy				
EC 290-1 Späne lieferbar; Chips available																	
CRM	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co	Cu	N	V	Ø 35x25 mm, wrought			
EC 274-1D	1.563	1.057	0.391	0.0148	0.0096	8.041	1.439	0.076	0.0033	(0.021)	0.0277	0.0770	3.952	Vanadiumstahl; V-Steel			
EC 274-1 Späne lieferbar; Chips available																	
CRM	C	Si	Mn	S	P	Cu	Ni	Cr	Ti	Ø 35x19 mm, cast							
2 T1/1	0.10	5.29	0.14	0.013	0.014	(<0.03)	0.036	0.065	0.02	Dynamostahl							
2 T2/1	0.026	3.24	0.18	0.017	0.009	0.09	0.11	0.03	-	Dynamo Steel							
2 T2/2	0.039	3.84	0.28	0.020	0.012	0.075	0.074	0.065	0.037								
2 T3/2	0.090	0.66	0.60	0.033	0.058	0.10	0.11	0.40	<0.01								
2 T4/1	0.17	1.97	0.23	0.041	0.012	0.16	0.077	0.24	<0.005								
CRM	C	Si	S	P	Mn	Cr	Ni	Cu	Mo	Ti	V	Al	Nb	Ø 35x19 mm, cast			
2 B16	0.16	1.95	0.051	0.068	2.05	0.26	3.74	0.09	0.11	0.075	0.53	0.037	0.11	Dynamostahl; Dynamo Steel			
CRM	C	Si	Mn	P	S	Cu	Ni	Cr	V	Mo	Sn	Al	Ø 31x19 mm				
3 1134	0.026	2.89	0.277	0.028	0.009	0.070	0.038	0.019	-	0.008	0.003	0.329	Dynamostahl	3 1134 Späne lieferbar			
3 1135	0.027	3.19	0.094	0.006	0.026	0.056	0.050	0.022	<0.01	0.014	0.004	0.0028	Dynamo Steel	Chips available			
CRM	C	Si	Mn	P	S	Cu	Cr	Ni	Mo	Al	As	Ti	N	Ø 35x30 mm, wrought			
EC 191-1D	0.013	3.14	0.026	0.011	0.0016	0.008	0.026	0.018	(0.002)	0.40	0.0031	0.0088	0.0026	Dynamostahl			
EC 186-1D	0.610	1.72	0.870	0.022	0.035	0.281	0.218	0.190	0.048	0.014	-	-	-	Dynamo Steel			
EC 191-1, EC 186-1 Späne lieferbar; Chips available																	
CRM	C	Si	Mn	P	S	Cr	Ni	Cu	Ti	Zr	B	Sn	Sb	N	Al	Al(sol) Ø 37x30 mm	
CI 11706-2	0.063	1.49	1.42	0.062	0.017	0.222	0.370	0.250	0.032	0.0084	0.013	0.033	0.0012	0.0062	0.465	0.460 Si-Stahl	
CI 11706-3	0.106	1.03	0.546	0.045	0.029	0.187	0.571	0.146	0.026	0.017	0.012	0.019	0.0012	(0.0058)	0.783	0.779 Si-Steel	
CI 11706-4	0.120	0.162	0.256	0.040	0.038	0.090	0.837	0.157	0.014	0.014	0.0090	0.017	(0.0004)	0.0025	1.47	1.46 nur Satz/set only	
CI 11706-5	0.040	4.16	1.10	0.020	0.031	0.042	0.101	0.063	0.010	0.0035	0.0054	0.0055	0.022	0.0026	0.068	0.065	
CI 11706-6	0.032	3.38	2.08	0.018	0.0087	0.627	0.060	0.351	0.037	0.0035	0.022	0.105	0.0011	0.0050	0.0067	0.0049	
CI 11706-7	0.036	2.47	1.75	0.061	0.011	0.492	0.159	0.278	0.043	0.023	0.021	0.072	0.0008	0.0042	1.18	1.17	
CI 11706-8	0.0041	1.59	0.242	0.015	0.0062	0.014	0.010	0.037	(0.0003)	0.0003	0.0024	0.0041	(0.0007)	0.0025	0.027	0.023	

RM	C	Si	S	P	Mn	Cr	Ni	Mo	Cu	Co	V	Al	W	Nb	Sn	As
4 15254X	0.335	1.001	0.029	0.055	0.899	2.26	1.042	0.795	0.408	0.642	0.182	0.037	0.339	0.29	0.050	0.024
4 15258N	0.548	1.020	0.070	0.0439	1.434	0.465	0.327	0.215	0.0934	0.272	0.218	0.032	0.102	0.103	0.0453	-
4 15261S	0.819	1.46	0.064	(0.085)	0.688	0.511	0.104	1.35	0.282	0.289	0.087	1.32	0.188	0.773	0.023	-

	Sb	Ti	N	Bi	Pb											
0.030	0.034	0.026	0.009	0.0055	Ø 43x20 mm cast											
-	0.120	-	-	-	Ø 42x15 mm, wrought											
-	0.471	-	-	-	Ø 40x15 mm, chill cast											

CRM	C	Si	Mn	P	S	Cr	Ni	Cu	Mo	Al	Ø 32x45 mm, wrought
-----	---	----	----	---	---	----	----	----	----	----	---------------------

CI 16705-1	0.200	0.140	0.203	(0.033)	(0.008)	2.03	0.443	0.084	0.406	0.381	Stahl, hoch Al
CI 16705-2	0.137	0.288	0.691	(0.013)	(0.004)	1.78	0.107	0.093	0.286	0.507	Steel, high Al
CI 16705-3	0.376	0.302	0.363	(0.018)	(0.022)	1.52	0.175	0.400	0.166	0.920	
CI 16705-4	0.237	0.225	0.473	(0.029)	(0.054)	1.14	0.116	0.269	0.112	1.19	nur Satz/set only
CI 16705-5	0.457	0.532	0.229	(0.015)	(0.010)	1.00	0.069	0.052	0.068	1.49	
CI 16705-6	0.323	0.122	0.161	(0.057)	(0.029)	1.36	0.325	0.175	0.218	0.64	

CRM	C	Si	Mn	P	S	Cr	Ni	Cu	Mo	V	Al	Ø 40x30 mm, wrought
-----	---	----	----	---	---	----	----	----	----	---	----	---------------------

CI 21703-1	0.425	1.49	0.155	0.0047	0.015	5.67	0.254	0.173	1.03	0.190	0.313	Gesenkstahl
CI 21703-2	0.474	1.32	0.324	0.026	0.0035	4.79	0.278	0.356	1.55	0.449	0.174	Die Steel
CI 21703-3	0.353	0.96	0.439	0.017	0.036	3.89	0.141	0.108	1.99	0.593	0.299	
CI 21703-4	0.315	1.15	0.73	0.025	0.015	3.43	0.131	0.040	2.43	0.86	0.235	nur Satz/set only
CI 21703-5	0.252	0.79	0.613	0.038	0.024	2.49	0.450	0.071	3.06	1.26	0.44	

RM	C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Co	Ti	Al	Fe	Ø 35x20 mm
----	---	----	----	---	---	----	----	----	----	----	----	----	----	------------

CT 045A	0.228	0.002	<0.010	0.001	<0.001	3.12	11.38	1.18	0.006	13.39	0.005	0.004	70.70	AerMet 100
---------	-------	-------	--------	-------	--------	------	-------	------	-------	-------	-------	-------	-------	------------

CRM	C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Co	V	Ti	Al	Nb	B	Sn	Sb	35x35x30mm
CT 070A	0.014	0.015	0.32	0.003	<0.001	5.54	24.47	0.006	0.010	29.00	0.043	0.82	0.47	4.63	0.0038	-	-	
CT 098A	0.025	0.037	0.39	0.003	<0.0005	0.099	37.53	0.021	0.026	14.46	0.002	1.54	0.050	5.06	0.0065	0.0011	0.0003	

CRM N Ø 35x19 mm

3 1755 0.01184 Stickstoff in Stahl, niedr. leg.
Nitrogen in Low Alloy Steel

3 1755 Späne lieferbar; Chips available

CRM N Al Ca Ø 40x40 mm

G 130	0.0153	0.0046	0.0024	N, Al + Ca in niedr. leg. Stahl	Späne lieferbar
G 131	0.0333	0.0043	-	N, Al + Ca in Low Alloy Steel	Chips available
G 132	0.0097	0.0021	0.0002		
G 133	0.0360	-	-		
G 134	-	0.0124	0.0005		
G 135	0.0238	0.0274	0.0008		
G 136	-	0.0034	0.00031		
G 137	0.0083	0.0017	0.00025		
G 138	0.0063	0.0022	-		
G 139	0.0113	(0.029)	0.0031		
G 140	0.0083	0.0307	0.0015		
G 141	0.0154	0.0071	-		

CRM N C Si Mn P S Cr Ni Mo Co Cu V W Ø 47x15 mm, HIP

J 49D 1.89 (1.0) (0.5) (0.4) (0.02) (0.01) (0.3) (0.2) (3.3) (0.3) (0.1) (5.1) (3.6) Vancron-Stahl, hoch N; Vancron Steel, high N

RM N(sol) N(insol) C Si Mn P S Al Cr Ø 35x20 mm

KW N-1	0.0012	0.0001	0.015	0.10	0.10	0.002	0.003	0.050	0.21	Stickstoff in Stahl, niedr. leg.
KW N-2	0.0048	0.0002	0.014	0.10	0.10	0.002	0.003	0.048	0.29	Nitrogen in Low Alloy Steel
KW N-3	0.0076	0.0003	0.012	0.10	0.10	0.002	0.003	0.048	0.19	
KW N-4	0.0110	0.0002	0.012	0.10	0.10	0.003	0.004	0.048	0.20	nur Satz/set only
KW N-5	0.0194	0.0008	0.012	0.10	0.11	0.003	0.004	0.050	0.41	

RM C Si S P Mn Ni Cr Mo Cu Nb N Ø 40x15 mm, chill cast

4 NSA1E	0.07	0.41	-	-	0.42	7.9	20.3	2.47	-	0.040	cast	Stickstoff in Edelstahl
4 NSA2G	0.142	0.805	0.0083	-	0.808	10.24	18.71	1.89	-	0.163		Nitrogen in Stainless Steel
4 NSA3J	0.16	0.57	-	-	1.07	12.0	16.1	2.8	-	0.20	wrought	
4 NSA4A	0.0262	0.44	0.0130	0.0281	5.59	17.11	23.79	4.19	0.487	0.079	0.532	
4 NSA5A	0.063	0.281	0.0212	(0.010)	4.27	9.52	20.73	2.32	0.098	0.574	0.340	
4 NSA6A	0.0132	0.258	0.0086	0.0183	1.59	31.32	26.93	6.75	1.16	0.053	0.188	
4 NSA7A	0.0209	0.359	0.0009	0.022	0.951	5.67	25.91	3.25	1.42	0.015	0.247	wrought

4 NSB1D	0.17	0.58	-	-	0.44	10.0	19.1	0.11	-	0.04	wrought	
4 NSB2D	0.06	0.66	-	-	0.62	11.1	18.2	0.21	-	0.095		
4 NSB3G	0.121	0.471	-	-	0.632	9.26	15.22	0.639	-	0.198		

RM C Si S P Mn Ni Cr Mo Cu Nb N V W Co Ø 40x17 mm, chill cast

4 NSC1M	0.350	0.90	0.0197	-	7.49	5.49	17.57	0.251	0.382	1.62	0.100	0.554	-	-	Stickstoff in Edelstahl
4 NSC2N	0.570	1.20	0.0233	-	8.36	4.00	20.14	0.782	1.040	2.25	0.269	0.293	-	-	Nitrogen in Stainless Steel
4 NSC3V	1.492	1.89	0.0098	-	10.97	3.03	24.71	0.086	0.114	2.47	0.478	0.126	-	-	
4 NSC4C	0.559	1.65	0.0100	-	8.98	6.94	31.88	1.28	0.197	3.15	0.896	0.197	0.192	0.215	
4 NSC5A	0.493	1.16	0.0095	-	2.49	4.16	22.47	0.002	0.745	2.31	0.257	0.026	-	-	
4 NSC6A	0.027	0.53	0.005	0.005	8.85	6.53	20.5	0.004	0.006	-	0.235	0.005	-	-	HIP

4 NSD1B	0.046	0.411	0.009	0.019	23.53	0.114	24.51	1.12	0.042	0.030	0.88	-	0.057	0.128	wrought Ø 38x15 mm
---------	-------	-------	-------	-------	-------	-------	-------	------	-------	-------	------	---	-------	-------	--------------------

Spezialstahl

(Special Steel)

CRM	C	Mn	P	S	Si	Cu	Ni	Cr	V	Mo	Co	Ti	Al	Nb	Ta					
3 1230	0.044	0.64	0.023	0.0007	0.43	0.14	24.2	14.8	0.23	0.18	0.15	2.12	0.24	(0.07)	-					
3 1233	0.502	9.16	0.031	0.002	0.219	0.375	3.43	21.08	0.096	0.237	-	-	-	-	-					
3 1250	0.022	0.052	<0.003	0.0025	0.097	0.022	37.78	0.077	0.077	0.014	16.1	1.48	0.99	2.99	0.003					
B Ø 31x19mm																				
0.0055 (<0.001) 0.0078	A286 Ventilstahl; Valve Steel	Stahl, hoch warmfest Steel, high temp.				3 1230 - 1250	Späne lieferbar; Chips available													
CRM	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	N	Sn	Ti	Zr	Ø 38x30 mm, wrought			
EC 285-2D	0.002	0.012	0.017	0.0053	0.0025	0.024	4.987	18.07	0.1067	0.0008	7.76	0.009	0.0007	0.001	0.520	0.005	Stahl, martensit. Maraging Steel			
CRM	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	N	Sn	Ti	V	Ø 38x12 mm, wrought			
6 161A	0.004	0.032	0.031	0.004	0.0007	0.12	4.82	18.40	0.14	0.0023	9.22	0.22	(0.002)	(0.0015)	0.65	0.031	Stahl, martensit. Maraging Steel			
RM	C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Co	Ti	Al	B	Ø 35x20 mm, wrought						
CT 250	0.002	0.006	0.008	0.003	0.002	0.008	18.44	4.88	0.008	7.54	0.41	0.058	0.0024	Maraging 250						
CT 300	0.005	0.032	0.030	0.005	0.004	0.034	18.51	4.97	0.047	9.07	0.69	0.12	0.0020	Maraging 300						
RM	C	Si	S	P	Mn	Ni	Cr	Mo	Co	Al	Ti	Ø 40x15 mm, cast								
4 14933R	0.008	0.05	0.014	0.023	0.17	16.8	0.022	3.83	11.4	<0.005	0.029	Stahl, martensitaushärtend								
4 14934P	0.009	0.13	0.014	0.028	0.30	17.8	0.16	4.7	8.5	0.022	0.67	Maraging Steel								
4 14935T	0.0105	0.441	0.055	0.036	0.494	18.96	0.745	5.61	7.17	(0.007)	0.106									
CRM	C	Mn	Si	P	S	Cr	Ni	Fe	Mo	Cu	Co	Ti	Se	35x35x20 mm						
CT 124A	0.011	0.73	0.40	0.007	0.006	0.079	48.07	50.65	0.009	0.015	0.012	-	0.167	High Perm 49-FM						
CT 136A	0.018	0.44	0.198	0.001	<0.001	0.002	44.92	54.27	<0.001	<0.001	0.009	-	-	High Perm 45						
CT 138A	0.002	0.48	<0.010	0.001	0.006	<0.001	39.98	58.53	<0.001	<0.001	0.64	0.34	-	Glass Sealing 42 Gas Free						
CT 139A	0.021	1.00	0.015	0.001	0.0005	0.004	41.69	57.10	<0.001	<0.001	0.066	-	-	Low Exp 42 Dumet Core Rod						
CT 141A	0.0199	0.31	0.28	0.001	<0.001	<0.001	47.16	52.12	<0.001	<0.001	0.030	-	-	High Perm 49						
RM	C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Co	Sn	Ø 35x20 mm								
CT V92510	-	0.25	0.15	0.008	-	0.070	31.54	0.006	0.020	5.22	0.001	N35								
CT X17842	0.077	0.31	0.24	0.006	0.002	0.71	30.00	0.011	0.023	0.026	-	Temp Comp 31								
CT X31777	0.001	0.042	<0.01	0.002	0.002	0.020	9.48	0.016	5.23	0.022	-	VAC 403								

Weitere hochlegierte Sonderstähle siehe unter Abschnitt 2.3. Edelstahl, aust./Edelstahl, hoch leg.
For more special steels see part 2.3. Stainless Steel, aust./Stainless Steel, high alloy

wrought

RM	Mn	Al	Co	Ni	W	Si	\varnothing 40x15 mm, cast
4 14045E	0.49	4 14931D 19.7	4 13584D 1.00	4 13589J 49.6	4 13674D 1.81	4 13604E 0.55	
4 14046D	0.89		4 13601D 5.59			4 13606F 3.1224	
			4 13602D 7.71				

	Cr	Mo	Nb	Ti	V	\varnothing 40x15 mm, cast
4 13765G	19.9	4 13754G 10.80	4 13767E 0.65	4 13759E 0.23	4 13700D 0.59	
			4 13664E 1.11	4 13762E 0.41		

RM	C	Si	S	P	Mn	Ni	Cr	Mo	Al	\varnothing 40x15 mm, cast
4 FC1A	(0.013)	(0.02)	(0.008)	(0.020)	(0.06)	(0.018)	0.45	(<0.005)	(0.067)	
4 FM1A	(0.019)	(0.01)	(0.008)	(0.011)	0.53	(0.015)	(0.015)	(<0.005)	(<0.005)	
4 FS1B	(0.021)	(0.02)	0.058	(0.003)	(0.05)	(0.015)	(0.015)	(<0.005)	(0.065)	

CRM ppm C ppm Si ppm Mn ppm S ppm Cr ppm Mo ppm N 36-39x26 mm (achteckig; octangular)

EC 098-1D 5.1 4.8 0.8 3.1 57.1 8.5 2.4

CRM C Si Mn P S Cr Mo Ni Al As B Co Cu N Nb Pb Sn

EC 097-1D 0.00025 (<0.01) 0.0064 0.0019 0.0022 0.0016 (<0.001) 0.0025 0.0027 0.0051 (<0.001) 0.0036 0.0020 0.0007 (<0.001) (<0.005) (<0.0025)

Ti V W Zr Bi Ca Mg O Sb Ta Zn Ø 38x30 + 39x3 mm, wrought

(<0.0015) (<0.001) (<0.001) (<0.001) (<0.005) (<0.005) (<0.005) (0.05) (0.001) (<0.0005) (<0.0001) **EC 097-1** Späne lieferbar; Chips available

CRM C Mn P S Si Cu Ni Cr V Mo Co Ti As Al B Pb W Sn

3 1265A 0.0067 0.0057 0.0011 0.0055 0.0080 0.0058 0.041 0.0072 0.0006 0.0050 0.0070 (0.0001) (0.0002) (0.0007) 0.00013 0.000015 <1ppm <5ppm

3 1768 0.0010 0.0014 0.0013 0.0003 (<0.0010) 0.0006 0.0014 (<0.0002) (<0.0001) (<0.0003) 0.0025 (<0.0010) (<0.0001) 0.0024 (<0.0002) (<0.0001) (<2ppm) (<1ppm)

Sb Ag Zn N Ge O H Fe Ø 31-35x19 mm

<0.5ppm (<1ppm) <0.2ppm <3ppm (<1ppm) <20ppm <50ppm <70ppm <5ppm – 99.9
– 20ppm – 360ppm – 99.9

CRM C Mn P S Si Cu Ni Cr Mo Al As Co N Sn Ti Ø 35x19 mm

6 50F 0.0064 0.082 0.0066 0.0031 0.016 0.0088 0.016 0.022 0.0017 0.003 0.0013 0.0023 0.0042 0.0010 0.0004 weitere 11 informative Werte im Zertifikat further 11 informative values in certificate

CRM C Si Mn P S Cr Ni Cu Al Ø 37x55 mm

CI 15704a-1 0.022 0.212 0.165 0.0043 0.010 0.017 0.027 0.021 0.29 nur Satz/set only

CI 15704a-2 0.013 0.0020 0.026 0.0032 0.022 0.0020 0.019 0.102 –

CI 15701a-3 0.018 0.061 0.063 0.0073 0.0092 0.0026 0.0209 0.074 0.129

CI 15701a-4 0.020 0.074 0.216 0.0068 0.006 0.009 0.021 0.023 0.39

CI 15701a-5 0.088 0.032 0.41 0.0167 0.0097 0.0032 0.0107 0.142 0.029

CRM C Si Mn P S Cr Ni Cu Al N Ø 40x60 mm

CI 15713-1 0.022 0.199 0.201 0.0072 0.0027 0.032 0.066 0.066 0.217 0.012 nur Satz/set only

CI 15713-2 0.013 0.0020 0.026 0.0032 0.022 0.0020 0.019 0.102 – –

CI 15713-3 0.018 0.061 0.063 0.0073 0.0092 0.0026 0.021 0.074 0.129 –

CI 15713-4 0.087 0.015 0.40 0.0064 0.016 0.0063 0.028 0.085 0.014 –

CI 15713-5 0.088 0.032 0.41 0.0167 0.0097 0.032 0.011 0.142 0.029 –

CRM C Si Mn P S Cr Ni Cu Al N Ø 40x60 mm

CI 15714-1 0.022 0.084 0.165 0.0043 0.010 0.017 0.027 0.021 0.029 – nur Satz/set only

CI 15714-2 0.017 0.214 0.151 0.010 0.0022 0.017 0.105 0.118 0.413 0.006

CI 15714-3 0.022 0.199 0.201 0.0072 0.0027 0.032 0.066 0.066 0.217 0.012

CI 15714-4 0.020 0.074 0.216 0.0068 0.006 0.0089 0.021 0.023 0.39 –

CI 15714-5 0.061 0.166 0.319 0.040 0.0050 0.022 0.020 0.020 0.284 0.014

CRM C Si Mn P S Cr Ni Cu Al N Ø 35x30 mm

CI 15715-1 0.012 0.017 0.034 0.0019 0.020 0.016 0.030 0.021 0.050 0.015 nur Satz/set only

CI 15715-2 0.027 0.180 0.195 0.014 0.0063 0.048 0.116 0.089 0.290 0.016

CI 15715-2 0.030 0.182 0.106 0.0061 0.025 0.147 0.182 0.123 0.205 0.011

CI 15715-4 0.061 0.341 0.254 0.021 0.0058 0.114 0.182 0.168 0.412 0.012

CI 15715-5 0.060 0.506 0.358 0.036 0.031 0.170 0.203 0.254 0.432 0.018

RM	C	Mn	Si	P	S	Cr	Ni	Mo	V	Ti	Cu	Al	Sn	W	Co	Nb	As	Zr
BR ST1	0.520	1.04	0.486	0.039	0.025	0.697	0.786	0.398	0.330	0.078	0.262	0.098	0.0165	0.139	0.052	0.056	0.031	0.025
BR ST2	1.075	2.38	0.340	0.040	0.013	2.35	0.603	0.128	0.156	0.013	0.242	0.016	0.033	0.194	0.013	0.086	0.027	0.005
BR ST3	0.252	1.85	1.16	0.018	0.007	0.217	1.01	0.048	0.083	0.002	0.520	0.013	0.083	0.386	0.103	0.007	0.023	0.002

B N Pb Sb Se Ø 45x30 mm

0.0057	0.0053	(0.001)	(0.01)	(0.004)
0.0018	(0.0085)	(0.001)	(0.002)	-
0.004	0.0076	(0.001)	(0.007)	-

RM	C	Si	Mn	P	S	Cr	Ni	Mo	Al	As	Co	Cu	Nb	Pb	Sn	Ti	V	W
SL CFe1	0.0040	0.0065	0.0385	0.0030	0.0025	0.0130	0.0220	<0.0010	0.0025	0.0015	0.0030	0.0100	0.0010	<0.0010	0.0005	0.0005	0.0003	<0.0002
SL CFe2	0.26	0.25	0.90	0.035	0.022	0.25	0.25	0.09	0.065	0.050	0.025	0.12	0.045	-	0.015	0.042	0.07	0.01
SL CFe3	0.04	0.44	1.57	0.024	0.017	18.1	10.6	2.1	0.007	-	0.32	0.23	0.55	-	0.017	0.02	0.098	0.087
SL CFe4	1.6	0.4	0.4	0.01	0.01	10.9	0.2	0.7	0.008	0.008	0.03	0.06	0.03	0.004	0.004	0.002	0.9	0.03
SL CFe9	0.09	0.001	1.2	0.06	0.3	0.01	0.01	0.005	0.0005	0.003	0.003	0.006	-	0.3	-	-	-	-

Zr Ca B Te Sb N Ø 35-40x30 mm + Ø 35-40x50 mm

<0.0002	<0.0001	0.0001	<0.0002	-	-
0.008	0.0028	0.0045	-	0.0036	0.0088
-	-	0.0004	-	-	-
0.003	0.0006	0.001	-	0.003	-
-	-	0.0001	-	0.0005	-

Kontrollproben für Argonsystem bei OES; Control samples for argon system in OES

Zur Kontrolle der Funkenkammer hinsichtlich Sauerstoff und Wasserstoffverunreinigung wird Brennfleck und Linienintensität zwischen der FeSi-Probe (SL CFe0) und einer Reineisenprobe z.B. SL RE12 oder 13 verglichen. Dabei sollen für eine hinreichend gute Entladungssatmosphäre bei HEPS/funkenähnlicher Entladung die nachstehend genannten Mindestintensitäten erreicht werden:
In order to check possible oxygen and hydrogen contamination in the sparking chamber the burning spot appearance and line intensity between the FeSi sample SL CFe0 and a pure iron sample e.g. SL RE12 or 13 is compared. This comparison shall result at HEPS/sparklike discharge in the following minimum line intensities for a satisfactory discharge atmosphere:

Fe 1877 > 60%, Fe 2730 > 70%, Fe 2813 oder Fe 3608 > 80%. Probe SL CFe0 - Si-Gehalt ca. 20%; Sample SL CFe0 - Si-content approx. 20% Ø 40x30 mm + Ø 40x50 mm

RM	C	Mn	Si	P	S	Cu	Cr	Ni	Al	Mo	W	V	Ti	Co	As	Sn	B	Nb
SP CM1A	0.79	1.97	0.16	0.023	0.011	0.14	0.52	0.48	0.12	0.07	0.07	0.082	0.055	0.03	0.028	0.005	0.0013	0.016
SP CM2A	0.20	0.97	1.66	0.10	0.012	1.01	1.50	1.20	0.03	0.33	0.23	0.10	0.34	0.43	0.11	0.08	0.0005	0.48
SP CM3A	0.295	0.37	0.27	0.016	0.0013	0.16	1.87	1.82	0.05	0.33	0.015	0.007	0.006	0.012	0.005	0.007	0.0002	0.006

Pb Sb N Zr Ta Ø 35-43x25 mm

-	0.01	0.008	-	-
0.06	0.008	-	0.03	0.027
-	-	0.007	-	-

B R E I T L Ä N D E R G M B H

2.8.2

Stahl, Kontrollproben

(Steel, Control Chart Samples)

RM	C	Mn	Si	P	S	Cu	Cr	Ni	Al	Mo	W	V	Ti	Co	As	Sn	Nb	N
SP SL1A	0.078	0.46	1.39	0.024	0.011	0.09	13.4	0.23	0.86	0.03	0.1	0.017	0.004	0.02	-	0.01	-	0.025
SP SL2A	0.015	1.84	0.64	0.025	0.027	0.50	16.9	11.0	0.005	2.03	0.03	0.075	0.06	0.09	0.008	0.01	-	0.04
SP SL3A	0.043	1.73	0.53	0.024	0.002	0.22	24.6	19.6	0.007	0.38	0.03	0.066	0.003	0.06	-	0.006	0.0013	0.065
SP SL4A	1.38	2.85	2.28	0.038	0.017	0.75	26.3	2.04	0.12	0.92	0.35	0.54	0.8	0.11	-	0.02	1.11	-
SP SL5A	0.37	5.8	0.36	0.021	0.014	2.90	11.7	4.94	0.035	4.12	0.78	0.21	0.004	0.26	0.005	0.004	0.20	-
SP SL6A	0.17	0.24	0.23	0.015	0.029	0.22	6.8	32.3	0.26	0.13	1.74	0.15	1.8	0.69	0.004	0.006	0.36	-
SP HS1A	0.72	0.28	0.28	0.023	0.011	0.08	4.15	0.14	0.03	0.06	17.5	1.33	0.003	4.7	-	0.02	-	-
SP HS2A	1.24	0.27	0.24	0.024	0.017	0.08	4.15	0.21	0.035	3.75	9.3	3.4	0.003	9.9	-	0.01	-	-

B Ta Ø 35-43x25 mm

- -
0.002 -
0.002 -
0.0013 -
- 0.07
- -
- -
- -

CRM	C	Mn	Si	P	S	Cu	Cr	Ni	Al	Mo	W	V	Ti	Co	As	Sn	B	Nb
SP SP1A	0.047	1.87	0.33	0.024	0.26	0.52	17.7	8.06	0.004	0.42	0.03	0.058	0.02	0.095	0.006	0.01	0.0007	0.012
SP SP2A	1.38	20.1	0.63	0.062	0.004	0.11	2.30	0.27	0.05	0.24	0.03	0.024	0.04	0.02	-	0.006	-	-
SP SP3A	0.27	0.29	0.72	0.023	0.008	0.62	15.1	5.65	0.08	0.24	0.12	0.10	0.13	0.02	-	0.01	0.88	-
SP SP5B	0.20	1.86	3.07	0.108	0.023	0.15	0.38	3.00	0.18	0.13	0.62	0.71	0.35	0.135	0.19	0.08	0.14	0.090
SP SP6A	0.10	0.38	4.65	0.017	0.009	0.12	0.11	0.04	0.32	0.01	0.02	0.016	0.008	0.003	0.003	0.01	-	-
SP SP7A	0.006	0.08	0.036	0.007	0.010	0.08	0.01	47.3	0.003	0.01	-	0.001	0.004	0.003	-	-	-	-
SP SP8B	2.37	0.86	1.40	0.022	0.012	0.075	37.6	2.72	0.13	0.10	0.05	0.13	0.13	0.075	0.05	0.06	0.03	0.04

Pb Sb Ø 35-43x25 mm

- -
- -
- -
- -
0.09 0.07
- -
- -
- -

CRM	C	Mn	Si	P	S	Cu	Cr	Ni	Al	Mo	W	V	Ti	Co	As	Sn	B	Nb
SP LA1A	0.007	0.13	0.008	0.004	0.011	0.027	0.042	0.014	0.001	0.003	0.001	0.001	0.001	0.002	0.002	0.010	0.0001	
SP LA2B	0.19	0.19	1.53	0.077	0.040	0.45	0.28	2.01	0.27	0.62	0.32	0.33	0.32	0.29	0.062	0.046	0.004	0.25
SP LA3B	0.67	0.75	0.76	0.036	0.030	0.13	1.05	1.09	0.04	0.34	0.135	0.205	0.072	0.115	0.084	0.046	0.008	0.07
SP LA4B	1.18	1.76	0.043	0.023	0.010	0.20	1.85	0.08	0.025	0.006	0.003	0.008	0.002	0.004	0.003	0.004	0.0002	0.09
SP LA5A	0.39	1.87	0.43	0.022	0.010	0.25	3.75	2.78	0.09	0.89	0.77	0.52	0.04	0.07	0.005	0.031	0.0005	0.05

Pb Sb Zr Ca Ta N Ø 35-43x25 mm

0.001 0.001 0.000 0.001 0.000 0.0045
0.05 0.047 - 0.003 - -
0.03 0.054 - 0.006 - 0.015
- - - - 0.008
- - 0.013 - - 0.012

SUS	C	Mn	Si	P	S	Ni	Cr	Cu	Mo	V	Co	W	As	Sn	Sb	Al	B	
1 DC	0.4	0.7	0.5	0.05	0.01	0.3	0.3	0.5	0.01	0.00	0.02	0.00	0.01	0.01	0.01	0.05	0.005	
1 163SUS	1.3	0.2	0.9	0.03	0.02	0.07	0.07	0.2	0.03	0.00	0.02	0.00	0.03	0.01	-	0.02	-	
1 165SUS	0.16	1.6	0.2	0.09	0.01	0.16	0.17	0.1	0.06	0.02	0.00	0.02	0.02	0.02	-	0.01	0.015	
Ti Ø 45x75, 150 + 300 mm, wrought																		
		0.025																
		0.10																
		0.01																
SUS	C	Si	Mn	P	S	Cr	Mo	Ni	V	W	Cu	Co	Nb	Ø 57x52 mm				
B SUS-1R	0.9	0.8	1.1	0.02	0.017	1.7	0.9	2.9	0.5	0.7	0.7	0.3	0.55	heißisostat. verdichtet; hot isostat. pressed				
SUS	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	Nb	Sn	Ti	V	W	
5 A	0.03	0.03	0.15	<0.005	0.005	0.02	<0.005	0.04	0.04	-	0.01	0.02	<0.005	<0.005	<0.005	<0.005	<0.005	
5 B	0.39	0.29	0.44	0.005	<0.005	1.2	0.20	1.5	0.01	0.001	0.02	0.15	0.005	0.01	0.01	0.01	0.005	
5 C	0.15	0.17	1.2	0.07	0.06	0.19	0.11	3.4	0.05	0.008	0.06	0.47	0.02	0.05	0.04	0.40	0.25	
5 D	0.80	0.83	0.40	0.01	0.03	3.0	1.3	0.10	0.19	<0.001	0.29	0.11	0.06	0.01	0.11	0.12	0.16	
5 E	0.07	0.29	0.53	0.005	<0.001	19.7	0.005	31.0	0.55	<0.001	0.04	0.005	<0.005	-	0.48	0.08	0.02	
5 F	0.02	0.19	0.46	0.02	<0.005	25.5	3.5	7.4	<0.005	0.002	-	0.58	<0.005	0.01	0.01	0.05	0.63	
5 G	0.03	0.33	1.6	0.03	0.03	16.5	2.2	11.4	<0.005	-	0.12	0.43	<0.005	<0.01	<0.005	0.06	0.04	
As Ca N Pb Ta Zr Ø 45x25, 75 + 150 mm, wrought																		
-	-	-	-	-	-													
0.005	<0.001	-	<0.001	-	-													
-	<0.001	0.004	-	-	-	0.05												
-	-	0.01	-	-	-													
-	-	0.01	-	-	-													
0.005	-	0.20	-	-	-													
-	<0.005	0.03	-	<0.005	<0.005													
SUS	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	Nb	Sn	Ti	V	N	O	wrought Ø 38x40 mm
6 SULF2	0.17	1.13	0.007	0.008	0.24	0.19	0.115	0.12	0.035	0.040	0.014	-	-	-	-	0.0074	0.002	
6 SULF3	0.17	0.83	0.008	0.011	0.22	0.07	3.25	0.11	0.017	0.021	0.010	-	0.005	0.002	0.0024	0.0067	0.002	
6 SU4130	0.29	0.55	0.015	0.020	0.25	0.104	0.090	0.97	0.16	0.030	0.006	-	-	-	-	0.0057	0.002	
6 SU9310	0.125	0.57	0.010	0.016	0.23	0.19	3.25	1.29	0.127	0.026	0.016	0.006	0.014	0.002	0.005	0.0102	0.002	
6 SU4620	0.21	0.58	0.010	0.023	0.23	0.14	1.69	0.15	0.26	0.022	0.009	0.008	0.008	0.002	0.002	0.0090	0.002	
6 SU8620	0.21	0.836	0.011	0.0216	0.29	0.084	0.485	0.547	0.185	0.033	0.005	-	0.006	-	Ca=0.0008	0.0072	0.0017	
SUS	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Ca	Co	Nb	Sn	Ti	V	N O	38x40 mm, wrought
6 SUP20	0.38	0.84	0.011	0.005	0.64	0.21	0.116	1.76	0.46	0.018	0.0016	0.011	0.003	0.011	0.006	0.010	0.0093	0.002
6 SU8740	0.41	0.92	0.014	0.014	0.24	0.14	0.44	0.51	0.225	0.019	-	0.012	-	0.007	-	0.0085	0.0016	

SUS	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	B	Co	Nb	Sn	Ti	V	N	O
6 SU321	0.055	1.67	0.016	0.023	0.63	0.21	10.15	17.18	0.22	0.19	-	0.16	-	0.004	0.45	0.13	0.012	0.002
6 SU347	0.056	1.61	0.030	0.027	0.51	0.16	9.43	17.26	0.39	0.005	0.0040	0.05	0.79	0.007	-	-	0.060	0.004
6 SU316L	0.021	1.70	0.035	0.025	0.39	0.405	12.27	17.58	2.09	0.005	-	0.21	-	-	-	0.044	0.091	0.005
6 SU309	0.077	1.68	0.027	0.0009	0.50	0.26	13.68	22.50	0.30	0.006	0.0030	0.13	0.027	0.007	-	0.065	0.095	0.005

SUS/RM	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Sn	Al	V	Co	W	N	O	Ø 38-44x150 mm
6 01	0.19	0.46	0.004	0.018	0.042	0.017	0.010	0.012	0.005	<0.002	0.006	-	-	-	0.0037	0.014	AISI 1020
6 02	0.41	0.82	0.018	0.023	0.26	0.05	0.02	0.07	0.01	0.003	<0.001	-	0.01	-	0.0069	0.0052	AISI 1040 RM
6 03	0.18	1.15	0.025	0.10	0.28	0.27	0.11	0.18	0.04	0.017	<0.001	-	0.02	0.001	0.011	0.0054	AISI 1117
6 04	0.39	1.02	0.016	0.072	0.17	0.09	0.12	0.20	0.09	0.006	0.028	-	-	-	0.0034	0.0024	
6 05	1.06	0.33	0.010	0.025	0.23	0.18	0.11	1.55	0.024	0.010	0.009	0.008	0.01	(0.001)	0.0057	0.0028	AISI E52100 RM

SUS	C	Mn	P	S	Si	Cu	Cr	Ni	Mo	Sn	Al	V	Nb	W	Ti	Co	Ø 32x17 mm
6 207	0.147	0.51	0.017	0.013	0.39	0.034	0.37	0.017	0.005	(0.003)	0.007	0.002	0.024	-	-	-	AISI 5115
6 211	1.08	0.47	0.026	0.013	0.62	0.098	1.44	0.103	0.042	-	0.030	0.014	0.006	-	-	-	AISI E52100
6 213	0.152	0.68	0.015	0.005	0.49	0.059	0.37	2.68	(0.008)	(0.002)	(0.04)	(0.004)	0.013	(0.006)	(0.002)	-	
6 214	0.10	0.65	0.019	0.012	0.34	0.10	0.21	3.70	0.02	(0.005)	0.025	(0.004)	(0.007)	<0.008	(0.002)	-	
6 224	0.11	0.60	0.024	0.019	1.32	0.07	12.8	0.75	0.056	-	0.007	0.013	0.02	0.004	-	0.03	

SUS	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	Al	Pb	Sn	Co	Ti	W	V
BR RH12	1.185	0.43	12.7	0.05	0.012	0.28	0.11	0.31	0.59	0.038	-	-	-	0.013	-	-
BR RH13	0.93	0.20	0.26	0.021	0.013	4.12	-	4.75	-	-	-	4.64	-	6.12	1.78	
BR RH18	1.35	0.35	0.39	0.04	0.014	4.1	1.4	0.78	0.19	-	-	4.55	0.007	11.63	3.63	
BR RH30	0.341	0.568	1.55	0.0054	0.000	19.7	12.9	1.46	0.082	0.038	0.028	0.011	-	0.014	-	0.095

Ø 40x40 mm, wrought

Mg	B	Ø 40x40 mm, wrought
-	-	
-	-	
0.009	-	
-	0.0051	

SUS	C	Mn	Si	P	S	Cr	Ni	V	Mo	Ti	Cu	Al	W	Co	Nb	Ø 40x30 + 40x150 mm, wrought
HB MW-04	0.48	0.63	0.17	0.005	0.017	4.3	0.53	1.54	6.0	-	-	-	0.45	11.8	-	
HB MW-06	0.25	1.12	0.25	0.014	0.008	10.40	19.84	-	0.51	-	0.04	-	0.42	-	1.33	
HB MW-10	0.12	0.65	0.32	0.013	0.010	27.95	1.13	-	-	1.38	2.35	-	-	-	0.60	
HB MW-23K	0.113	0.73	1.70	0.016	0.011	23.69	0.59	-	-	-	0.26	0.75	-	-	-	

SUS	C	Si	S	P	Mn	Ni	Cr	Mo	Cu	Co	Sn	Al	Nb	W	As	Ti	V	Zr
SL RH12	0.4	0.5	<0.001	0.03	18	0.28	4.1	0.2	0.09	<0.001	0.02	<0.01	0.04	0.06	0.02	<0.001	0.02	0.02
SL RH13	1	0.4	<0.01	0.02	0.3	0.3	3.7	4.7	0.10	4	0.01	0.02	0.03	6	-	0.003	1.6	-
SL RH18	1.3	0.4	0.02	0.02	0.3	0.2	4	3.3	0.13	10	0.01	0.008	0.03	9	-	0.008	3	-
SL RH31	0.05	0.7	0.01	0.01	0.8	19	18	2	2	0.1	<0.01	0.007	0.5	0.3	<0.001	0.01	0.14	0.013
SL RH32	0.1	0.5	<0.01	<0.01	1.5	22	27	3	-	18	-	0.2	-	2.8	-	-	-	-
SL RH33	0.006	0.15	0.02	0.01	8.6	18.51	17.44	0.01	2.15	0.022	<0.01	0.01	0.54	0.09	<0.001	0.36	0.05	0.01
SL RN13	1.0	0.02	<0.01	<0.01	1.8	3	0.01	<0.01	<0.01	<0.01	0.05	0.4	<0.01	0.06	<0.01	<0.001	<0.01	0.16
SL RN14	0.08	1.7	0.10	0.09	0.1	0.05	3	0.5	0.4	0.5	0.014	0.004	0.5	0.4	0.05	0.07	0.6	0.002
SL RN15	3.0	-	-	1.8	-	3.0	-	-	-	-	0.05	0.4	-	-	-	-	-	-
SL RN16	1	0.02	<0.01	<0.01	1.8	3	0.01	<0.01	<0.01	<0.01	0.05	0.4	<0.01	0.06	0.01	<0.001	<0.01	0.16
SL RN17	0.02	1.8	>0.1	0.09	0.24	0.08	3.5	0.5	0.4	0.4	0.006	0.005	0.4	0.3	0.06	0.1	0.5	0.003
SL RN18	1	0.3	0.2	-	1.4	11.6	-	-	7	-	0.2	<0.01	-	-	-	-	-	-
SL RN19	1	1.2	0.1	0.1	1.5	3	3	1	0.5	0.8	0.1	0.5	0.5	0.5	0.05	0.1	0.5	0.1

B	Pb	La	N	Ta	Sb	Ca	Te	Bi	Ø 40x40 mm, wrought
-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	
-	-	-	-	-	-	-	-	-	Fe=68
-	-	-	-	-	-	-	-	-	
0.002	-	>0.03	0.1	0.5	-	-	-	-	
-	0.09	-	-	-	-	-	-	-	
<0.001	<0.01	-	<0.01	<0.01	0.04	<0.001	<0.01	<0.001	
0.006	<0.01	-	0.02	0.16	0.02	0.002	0.03	0.04	
-	-	-	-	-	0.04	-	-	-	
<0.001	<0.01	-	<0.01	<0.01	0.04	<0.001	<0.01	<0.001	
0.007	0.02	-	0.03	0.2	0.02	0.002	0.04	0.02	
-	0.3	-	-	-	-	-	0.05	0.05	
0.01	0.03	-	0.02	0.5	0.08	<0.001	0.05	0.03	

SUS	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	Co	Sn	Al	Nb	W	As	Ti	V	Zr		
IA QAA	0.01	0.01	0.003	0.002	0.001	0.01	0.01	0.01	0.001	0.004	0.0005	0.0002	0.001	0.005	0.003	0.0001	0.002	0.005		
IA QAC	0.05	0.1	2	0.1	0.07	0.1	5	0.1	0.6	0.01	0.1	0.003	<0.0001	0.7	0.1	0.01	1	<0.001		
IA QAD	0.9	2	0.02	0.003	0.002	5	2.8	1.5	0.6	1	0.06	0.2	0.4	0.01	0.01	1.7	0.3	0.002		
B Ca Pb N Ta Sb Ø 36x38 mm, wrought																				
<0.0001	0.0001	0.004	0.0005	0.01	0.006															
0.0004	<0.0001	<0.001	0.007	0.02	0.02															
0.01	<0.0001	0.003	0.002	0.01	0.1															
RM N C Si Mn P S Cu Ni Cr Mo Ø 35x20 mm (2x A-20 + 2 x B-20)																				
KW A-20	0.033	0.05	0.03	0.01	0.002	0.002	0.01	0.01	3.80	0.01	N in Stahl, niedr. leg.; N in Low Alloy Steel									
KW B-20	0.0015	0.01	0.01	0.001	0.002	0.002	0.01	0.01	0.01	0.01	nur Satz/set only									
SUS C Mn P S Si Cu Ni Cr Mo Al(sol) Al(ins) V Co As Nb Ti																				
KW A-g	1.00	0.01	0.001	0.001	0.06	0.10	4.04	-	-	0.077	0.001	0.03	-	-	0.11	0.30				
KW B-g	0.01	0.54	0.045	-	0.58	0.70	0.52	3.98	0.20	-	-	-	0.01	0.043	-	0.03				
KW C-g	0.11	1.96	-	0.028	-	-	-	0.49	0.98	0.016	0.001	0.48	0.20	-	-	-				
Sn Ca B W Ø 35x20 mm, wrought																				
-	-	-	0.21																	
0.086	0.0033	0.0093	-																	
-	-	-	-																	
SUS C Mn P S Si Cu Ni Cr Mo Al(sol) Al(ins) Ti Co As Nb Pb Ta Ø 35x20 mm, wrought																				
KW D-c	0.093	1.01	0.007	0.027	0.50	0.019	4.06	27.12	0.051	0.046	0.004	0.045	0.026	0.14	0.10	0.014	0.007	Edelst.		
KW E-c	0.055	1.45	0.010	0.008	1.57	0.060	14.74	15.71	2.40	0.030	0.002	0.15	0.21	0.077	0.41	0.14	0.22	St.Steel		
KW F-c	0.027	0.20	0.034	0.006	0.48	0.023	29.69	4.07	0.91	0.016	0.001	0.54	0.051	0.001	1.55	0.005	0.082	Satz/set		
SUS C Mn P S Si Cu Ni Cr Mo Al(sol) Al(ins) Ti Co As Nb Ø 35x20 mm, wrought																				
KW G-b	0.031	1.37	0.029	0.005	1.26	0.19	3.87	11.85	1.14	0.086	0.005	0.30	0.19	0.075	0.98	Edelstahl				
KW H-b	0.088	0.47	0.009	0.010	0.50	0.04	0.57	17.95	0.49	0.031	0.005	0.094	0.054	0.011	0.094	Stainless Steel				
KW I-b	0.26	0.19	0.004	0.028	0.22	<0.01	0.02	24.47	0.048	0.001	0.004	0.013	0.006	0.002	0.007	nur Satz/set only				
SUS C Si Mn Cr W Mo Co V P S Ni Cu Al Ø 40x40 mm, HIP-Technik; HIP-Technology																				
HM 12379	1.6	0.3	0.4	11.5	-	0.8	-	0.8	0.01	0.01	0.2	0.06	0.01	Stahl, SUS						
HM 12083	0.4	0.8	0.5	13.6	-	-	-	0.3	0.01	0.01	0.1	-	-	Steel, SUS						
HM 12842	0.9	0.3	2.0	0.4	-	-	-	0.1	0.01	0.01	0.1	0.04	0.01							
HM X245	2.45	0.9	0.5	5.3	-	1.3	-	9.6	-	-	-	-	-	Stangen bis zu 1 m Länge erhältlich						
HM 235Cr	2.3	-	-	20.0	-	1.0	-	4.2	-	-	-	-	-	Bars up to 1 m length available						
HM T15Mo	1.6	-	-	4.0	12	1.0	5	5.0	-	-	-	-	-							